



Product Data Sheet Urathix™ B3200 60BAC

Thixotropic short oil alkyd, modified with linoleic rich fatty acids

Applications

- general industrial coatings
- stoving enamels
- drum coatings
- one layer thick coatings
- anti sag/settling additive

Principal properties

- broad compatibility
- combination with aminos
- combination with isocyanates
- thixotropic

Dilutability

Xylene	complete
White Spirit	limited
Solvesso 100 ¹⁾	complete
Solvesso 150 ¹⁾	complete
n-Butyl acetate	complete
1-Methoxy 2-propyl acetate	complete
Methyl ethyl ketone	complete

Delivery form:

60% in Butylacetate

Product specifications

Property	Value	Unit	TM
Rheology	Rheology curve		2312
Acid value, on solid	Below 15	mg KOH/g	2401
Solid content	58 - 62	%	2026Q

Other product properties

Property	Range	Unit	TM
Appearance	Hazy	-	2265
Oil length	32	%	-
Type of oil	Linoleic rich	-	-
Density, 23 °C	ca. 970	kg/m ³	2160
Hydroxyl content (solid)	ca. 1,9	%	2432

Storage guidelines

The resin should be stored indoors in the original, unopened and undamaged containers in a dry place at storage temperatures between 5° C and 30° C. Exposure to direct sunlight should be avoided.

Shelf life

Under the stipulated storage conditions, the anticipated shelf-life is 365 days from last quality control date, as stated in the Certificate of Analysis

Material safety

A material safety data sheet of the products is available on request.

Test methods

Test methods (TM) referred to in the tables are available on request.

¹⁾ Exxon Chemicals

