

# RADILON AESTUS T1 RV500RKC 106 NT

PRELIMINARY

## DESCRIPTION

PPA injection moulding grade 50% glass fibre reinforced with high glass transition temperature and high melting point. Natural colour.

Suitable for parts requiring very high stiffness and strength. High resistance to hot water contact, suitable for drinking water contact.

ISO 1043: PA6T/6I-GF50

REGIONAL AVAILABILITY: North America, Europe, Asia Pacific, South and Central America, Near East/Africa

*THE CHARACTERISTICS SHOWN HERE MUST BE CONSIDERED PRELIMINARY AND INDICATIVE FOR A PRODUCT AT DEVELOPMENTAL STAGE*

## MATERIAL HANDLING AND PROCESSING

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.10%. Typical conditions with a desiccant drier: temperature 120° C, dew point -20 ° C or below, time 4 h or more. Avoid excessive shear rates and high thermal stresses for better processing. Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

Injection Molding Processing Parameters

Melt Temperature  
320 - 340°C

Mold Temperature  
130 - 160°C

Injection Speed  
high

## PRODUCT SAFETY AND APPROVALS

For safety instruction please refer to Material Safety Data Sheet

ROHS compliant 2011/65/EU and following amendments

Suitable for materials and articles intended to come into contact directly or indirectly with food in compliance with EU 10/2011

Suitable and approved for drinking water contact.

Please get in contact with our Customer Service for drinking water contact approvals and further information.



# RADILON AESTUS T1 RV500RKC 106 NT

PROPERTY	STANDARD	UNIT	VALUE	
			DAM*	Cond**
<b>PHYSICAL PROPERTIES</b>				
Density	ISO 1183	kg/m <sup>3</sup>	1620	
Moulding shrinkage - Parallel / Normal	ISO 294-4	%	0.1 / 0.5	
Water Absorption, 24h immersion at 23°C	ISO 62	%	0.1	
Moisture Absorption 23°C - 50%RH	ISO 62	%	1.1	
<b>MECHANICAL PROPERTIES</b>				
Tensile Modulus	ISO 527-2/1A	MPa	19000	18400
Stress at Break	ISO 527-2/1A	MPa	270	260
Strain at Break	ISO 527-2/1A	%	2.1	2.3
Flexural Modulus	ISO 178	MPa	18900	18500
Flexural Strength	ISO 178	MPa	430	410
Charpy Impact Strength	ISO 179/1eU	kJ/m <sup>2</sup>	104	107
Charpy Notched Impact Strength	ISO 179/1eA	kJ/m <sup>2</sup>	15	15.5
<b>THERMAL PROPERTIES</b>				
Melting Temperature	ISO 11357-1/-3	°C	310	
Heat Deflection Temperature	ISO 75/2Af	°C	282	
<b>ELECTRICAL PROPERTIES</b>				
Volume Resistivity	IEC 62631-3-1	Ohm*m	1E13	1E11
Surface Resistivity	IEC 62631-3-2	Ohm	1E12	1E10

\*: DAM = Dry As Moulded state according to ISO 16396-2, \*\*: Cond = Conditioned state similar to ISO 1110

1: Melt Temperature [°C] / Mold Temperature [°C] / Cavity Pressure [MPa]

