

# RADIFLAM B RV300K AE 135 NT

PROVISIONAL

## DESCRIPTION

PBT flame retardant injection moulding grade. 30% glass fibre reinforced. Natural colour.

Suitable for parts requiring fire retardancy along with high stiffness and good mechanical resistance. Rated V-0 according to UL-94.

ISO 1043: PBT-GF30 FR(17)

REGIONAL AVAILABILITY: North America, Europe, Asia Pacific, South and Central America, Near East/Africa

*THE CHARACTERISTICS SHOWN HERE ARE PROVISIONAL AND REFLECT THE AVERAGE VALUES OF PROPERTIES MEASURED OVER A LIMITED NUMBER OF PRODUCTION CAMPAIGNS*

## MATERIAL HANDLING AND PROCESSING

The material is delivered in moisture-proof packaging. It is important to dry the material prior to processing: maximum recommended water content is 0.02%. Typical conditions with a desiccant drier: temperature 120 ° C, dew point -40 ° C or below, time 2-4 h or more. Avoid excessive shear rates and high thermal stresses for better processing. Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

Injection Molding Processing Parameters

Melt Temperature  
250 - 280°C

Mold Temperature  
80 - 90°C

Injection Speed  
medium-high

## PRODUCT SAFETY AND APPROVALS

For safety instruction please refer to Material Safety Data Sheet  
Underwriters Laboratories Inc. certified material [www.ul.com](http://www.ul.com)  
ROHS compliant 2011/65/EU and following amendments



# RADIFLAM B RV300K AE 135 NT

PROPERTY	STANDARD	UNIT	VALUE
<b>PHYSICAL PROPERTIES</b>			
Density	ISO 1183	kg/m <sup>3</sup>	1670
Melt Flow Rate	ISO 1133	g/10min	3.8
Moulding shrinkage - Parallel / Normal	ISO 294-4	%	0.4 / 0.9
<b>MECHANICAL PROPERTIES</b>			
Tensile Modulus	ISO 527-2/1A	MPa	10600
Stress at Break	ISO 527-2/1A	MPa	140
Strain at Break	ISO 527-2/1A	%	2.7
Flexural Modulus	ISO 178	MPa	9700
Flexural Strength	ISO 178	MPa	215
Charpy Impact Strength	ISO 179/1eU	kJ/m <sup>2</sup>	62
Charpy Notched Impact Strength	ISO 179/1eA	kJ/m <sup>2</sup>	9.5
<b>THERMAL PROPERTIES</b>			
Melting Temperature	ISO 11357-1/-3	°C	225
Heat Deflection Temperature	ISO 75/2Af	°C	205
Heat Deflection Temperature	ISO 75/2Bf	°C	220
Vicat Softening Temperature	ISO 306	°C	210
<b>FLAMMABILITY PROPERTIES</b>			
Flammability	UL 94	class	V-0
Glow Wire Flammability Index	IEC 60695-2-12	°C	960
Glow Wire Flammability Index	IEC 60695-2-12	°C	960
Automotive Interior Flammability	ISO 3795	mm/min	0
<b>ELECTRICAL PROPERTIES</b>			
Volume Resistivity	IEC 62631-3-1	Ohm*m	1E13
Surface Resistivity	IEC 62631-3-2	Ohm	1E12
Comparative Tracking Index	IEC 60112	V	275

1: Temperature [°C] / Load [kg]

2: Melt Temperature [°C] / Mold Temperature [°C] / Cavity Pressure [MPa]

