

# RADILON AESTUS T1 RV400FC 106K NT

PROVISIONAL

## DESCRIPTION

PPA injection moulding grade 40% glass fibre reinforced with high glass transition temperature and high melting point. Natural colour.

Suitable for parts requiring high stiffness and strength. Appropriate for foodstuff contact, especially for kitchen tools, and for fuel cell components thanks to its high purity.

ISO 1043: PA6T/6I-GF40

REGIONAL AVAILABILITY: North America, Europe, Asia Pacific, South and Central America, Near East/Africa

*THE CHARACTERISTICS SHOWN HERE ARE PROVISIONAL AND REFLECT THE AVERAGE VALUES OF PROPERTIES MEASURED OVER A LIMITED NUMBER OF PRODUCTION CAMPAIGNS*

## MATERIAL HANDLING AND PROCESSING

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.10%. Typical conditions with a desiccant drier: temperature 120° C, dew point -20 ° C or below, time 4 h or more. Avoid excessive shear rates and high thermal stresses for better processing. Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

### Injection Molding Processing Parameters

Melt Temperature  
330 - 350°C

Mold Temperature  
140 - 160°C

Injection Speed  
high

## PRODUCT SAFETY AND APPROVALS

For safety instruction please refer to Material Safety Data Sheet

ROHS compliant 2011/65/EU and following amendments

Suitable to be in contact with foodstuff. Please get in contact with our Customer Service for further information.



# RADILON AESTUS T1 RV400FC 106K NT

PROPERTY	STANDARD	UNIT	VALUE	
			DAM*	Cond**
<b>PHYSICAL PROPERTIES</b>				
Density			1520	
Moulding shrinkage - Parallel / Normal	330/140/60 <sup>[1]</sup>	ISO 1183 ISO 294-4	%	0.2 / 0.7
Water Absorption, 24h immersion at 23°C	2mm	ISO 62	%	0.1
<b>MECHANICAL PROPERTIES</b>				
Tensile Modulus	1mm/min	ISO 527-2/1A	MPa	15800
Stress at Break	5mm/min	ISO 527-2/1A	MPa	245
Strain at Break	5mm/min	ISO 527-2/1A	%	1.9
Flexural Modulus	2mm/min	ISO 178	MPa	13500
Flexural Strength	2mm/min	ISO 178	MPa	360
Charpy Impact Strength	+23°C	ISO 179/1eU	kJ/m <sup>2</sup>	80
Charpy Impact Strength	-30°C	ISO 179/1eU	kJ/m <sup>2</sup>	69
Charpy Notched Impact Strength	+23°C	ISO 179/1eA	kJ/m <sup>2</sup>	15
Charpy Notched Impact Strength	-30°C	ISO 179/1eA	kJ/m <sup>2</sup>	15
<b>THERMAL PROPERTIES</b>				
Melting Temperature	10°C/min	ISO 11357-1/-3	°C	320
Heat Deflection Temperature	1.80 MPa	ISO 75/2Af	°C	293
<b>FLAMMABILITY PROPERTIES</b>				
Flammability	0.8mm	UL 94	class	HB
<b>ELECTRICAL PROPERTIES</b>				
Volume Resistivity	500V	IEC 62631-3-1	Ohm*m	1E13
Surface Resistivity	500V	IEC 62631-3-2	Ohm	1E12

\*: DAM = Dry As Moulded state according to ISO 16396-2, \*\*: Cond = Conditioned state similar to ISO 1110


1: Melt Temperature [°C] / Mold Temperature [°C] / Cavity Pressure [MPa]



# RADILON AESTUS T1 RV400FC 106K NT

## DIAGRAMS

### Stress-strain (dry)



### Secant modulus-strain (dry)

