

RADIFLAM A RV300 HF 533 RD

PRELIMINARY

DESCRIPTION

PA66 flame retardant injection moulding grade. Halogen and red phosphorus free. 30% glass fibre reinforced and heat stabilized. Red colour.

Suitable for parts requiring fire retardancy along with high stiffness and good mechanical resistance. Good electrical insulating properties. Rated V-0 according to UL-94.

ISO 1043: PA66-GF30 FR(40)

REGIONAL AVAILABILITY: North America, Europe, Asia Pacific, South and Central America, Near East/Africa

THE CHARACTERISTICS SHOWN HERE MUST BE CONSIDERED PRELIMINARY AND INDICATIVE FOR A PRODUCT AT DEVELOPMENTAL STAGE

MATERIAL HANDLING AND PROCESSING

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.10%. Typical conditions with a desiccant drier: temperature 80 °C, dew point -20 °C or below, time 2-4 h or more. Avoid excessive shear rates and high thermal stresses for better processing. Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

Injection Molding Processing Parameters

Melt Temperature
275 - 290°C

Mold Temperature
80 - 90°C

Injection Speed
medium-high

PRODUCT SAFETY AND APPROVALS

For safety instruction please refer to Material Safety Data Sheet

Underwriters Laboratories Inc. certified material www.ul.com

ROHS compliant 2011/65/EU and following amendments



RADIFLAM A RV300 HF 533 RD

PROPERTY		STANDARD	UNIT	VALUE DAM*	Cond**
PHYSICAL PROPERTIES					
Density		ISO 1183	kg/m ³	1420	
Water Absorption, immersion at 23°C	2mm	ISO 62	%		4.3
Moisture Absorption 23°C - 50%RH	2mm	ISO 62	%		1.3
MECHANICAL PROPERTIES					
Tensile Modulus	1mm/min	ISO 527-2/1A	MPa	10250	
Stress at Break	5mm/min	ISO 527-2/1A	MPa	130	
Strain at Break	5mm/min	ISO 527-2/1A	%	2.3	
Flexural Modulus	2mm/min	ISO 178	MPa	10500	
Flexural Strength	2mm/min	ISO 178	MPa	200	
Charpy Impact Strength	+23°C	ISO 179/1eU	kJ/m ²	46	
THERMAL PROPERTIES					
Melting Temperature	10°C/min	ISO 11357-1/-3	°C	260	
FLAMMABILITY PROPERTIES					
Flammability	0.8mm	UL 94	class		V-0
Glow Wire Flammability Index	2mm	IEC 60695-2-12	°C		960
Automotive Interior Flammability	3mm	ISO 3795	mm/min		0
ELECTRICAL PROPERTIES					
Volume Resistivity	500V	IEC 62631-3-1	Ohm*m	1E13	1E11
Surface Resistivity	500V	IEC 62631-3-2	Ohm	1E12	1E10

*: DAM = Dry As Moulded state according to ISO 16396-2, **: Cond = Conditioned state similar to ISO 1110

