

# RADIFLAM A RV250Z AF 325 BK

PRELIMINARY

## DESCRIPTION

PA66 flame retardant injection moulding grade with red phosphorus. 25% glass fibre reinforced. Improved impact properties at low temperature. Black colour.

Suitable for parts requiring fire retardancy along with medium stiffness and good mechanical resistance. Rated V-0 at 1.60 mm according to UL-94.

ISO 1043: PA66-GF25 FR(52)

REGIONAL AVAILABILITY: North America, Europe, Asia Pacific, South and Central America, Near East/Africa

*THE CHARACTERISTICS SHOWN HERE MUST BE CONSIDERED PRELIMINARY AND INDICATIVE FOR A PRODUCT AT DEVELOPMENTAL STAGE*

Formerly Known As LX22422

## MATERIAL HANDLING AND PROCESSING

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.10%. Typical conditions with a desiccant drier: temperature 80 ° C, dew point -20 ° C or below, time 2-4 h or more. Avoid excessive shear rates and high thermal stresses for better processing. Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored. The material can not be used to produce parts operating in hot and humid environments (> 70°C / 160°F), or in contact with hot water or overheated steam.

### Injection Molding Processing Parameters

Melt Temperature  
280 - 300°C

Mold Temperature  
80 - 100°C

Injection Speed  
medium-high

## PRODUCT SAFETY AND APPROVALS

For safety instruction please refer to Material Safety Data Sheet  
Underwriters Laboratories Inc. certified material [www.ul.com](http://www.ul.com)  
ROHS compliant 2011/65/EU and following amendments



# RADIFLAM A RV250Z AF 325 BK

PROPERTY	STANDARD	UNIT	VALUE	
			DAM*	Cond**
<b>PHYSICAL PROPERTIES</b>				
Density	ISO 1183	kg/m <sup>3</sup>	1300	
Water Absorption, immersion at 23°C	ISO 62	%		5.5
Moisture Absorption 23°C - 50%RH	ISO 62	%		1.2
<b>MECHANICAL PROPERTIES</b>				
Tensile Modulus	ISO 527-2/1A	MPa	7000	
Stress at Break	ISO 527-2/1A	MPa	105	
Strain at Break	ISO 527-2/1A	%	5.3	
Flexural Modulus	ISO 178	MPa	6200	
Flexural Strength	ISO 178	MPa	170	
Charpy Impact Strength	ISO 179/1eU	kJ/m <sup>2</sup>	88	
Charpy Impact Strength	ISO 179/1eU	kJ/m <sup>2</sup>	84	
Charpy Notched Impact Strength	ISO 179/1eA	kJ/m <sup>2</sup>	25	
Charpy Notched Impact Strength	ISO 179/1eA	kJ/m <sup>2</sup>	15	
<b>THERMAL PROPERTIES</b>				
Melting Temperature	ISO 11357-1/-3	°C	260	
Heat Deflection Temperature	ISO 75/2Af	°C	230	
Vicat Softening Temperature	ISO 306	°C	240	
<b>FLAMMABILITY PROPERTIES</b>				
Flammability	UL 94	class		V-0
Glow Wire Flammability Index	IEC 60695-2-12	°C		960
Glow Wire Flammability Index	IEC 60695-2-12	°C		960
Glow Wire Ignition Temperature	IEC 60695-2-13	°C		775
Automotive Interior Flammability	ISO 3795	mm/min		0
<b>ELECTRICAL PROPERTIES</b>				
Volume Resistivity	IEC 62631-3-1	Ohm*m	1E13	1E11
Surface Resistivity	IEC 62631-3-2	Ohm	1E12	1E10
Comparative Tracking Index	IEC 60112	V	600	

\*: DAM = Dry As Moulded state according to ISO 16396-2, \*\*: Cond = Conditioned state similar to ISO 1110

