

RADILON A CW250UK 3031 BK

DESCRIPTION

PA66 25% mineral filled injection moulding grade. Improved UV resistance. Black colour.

Suitable for parts requiring good dimensional stability, reduced shrinkage and low warpage. Intended to resist to outdoor exposure.

ISO 1043: PA66-MD25

REGIONAL AVAILABILITY: North America, Europe, Asia Pacific, South and Central America, Near East/Africa

MATERIAL HANDLING AND PROCESSING

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.15%. Typical conditions with a desiccant drier: temperature 80 ° C, dew point -20 ° C or below, time 2-4 h or more. Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

Injection Molding Processing Parameters

Melt Temperature
280 - 300°C

Mold Temperature
80 - 100°C

Injection Speed
medium-high

PRODUCT SAFETY AND APPROVALS

For safety instruction please refer to Material Safety Data Sheet
ROHS compliant 2011/65/EU and following amendments



RADILON A CW250UK 3031 BK

PROPERTY	STANDARD	UNIT	VALUE	
			DAM*	Cond**
PHYSICAL PROPERTIES				
Density	ISO 1183	kg/m ³	1340	
Melt Volume-Flow Rate	ISO 1133	cm ³ /10min		66
Melt Flow Rate	ISO 1133	g/10min		76
Moulding shrinkage - Parallel / Normal	ISO 294-4	%	0.5 / 0.9	
Water Absorption, immersion at 23°C	ISO 62	%		6.4
Moisture Absorption 23°C - 50%RH	ISO 62	%		1.5
MECHANICAL PROPERTIES				
Tensile Modulus	ISO 527-2/1A	MPa	7000	3000
Stress at Break	ISO 527-2/1A	MPa	90	55
Strain at Break	ISO 527-2/1A	%	5	25
Flexural Modulus	ISO 178	MPa	6600	2800
Flexural Strength	ISO 178	MPa	165	80
Charpy Impact Strength	ISO 179/1eU	kJ/m ²	65	
Charpy Impact Strength	ISO 179/1eU	kJ/m ²	35	
Charpy Notched Impact Strength	ISO 179/1eA	kJ/m ²	4.5	
THERMAL PROPERTIES				
Melting Temperature	ISO 11357-1/-3	°C		260
FLAMMABILITY PROPERTIES				
Flammability	UL 94	class		HB
Automotive Interior Flammability	ISO 3795	mm/min		0
ELECTRICAL PROPERTIES				
Volume Resistivity	IEC 62631-3-1	Ohm*m	1E13	1E11
Surface Resistivity	IEC 62631-3-2	Ohm	1E12	1E10

*: DAM = Dry As Moulded state according to ISO 16396-2, **: Cond = Conditioned state similar to ISO 1110

1: Temperature [°C] / Load [kg]

2: Temperature [°C] / Load [kg]

3: Melt Temperature [°C] / Mold Temperature [°C] / Cavity Pressure [MPa]

