

# RADILON MIXLOY S RVA150 100 NT

PRELIMINARY

## DESCRIPTION

PA6/ABS blend, 15% glass fibre injection moulding grade. Natural colour.

Suitable for parts requiring improved stiffness and low moisture absorption. Excellent aesthetic surface aspect.

ISO 1043: (PA6+ABS)-GF15

REGIONAL AVAILABILITY: North America, Europe, Asia Pacific, South and Central America, Near East/Africa

*THE CHARACTERISTICS SHOWN HERE MUST BE CONSIDERED PRELIMINARY AND INDICATIVE FOR A PRODUCT AT DEVELOPMENTAL STAGE*

Formerly Known As LX19122

## MATERIAL HANDLING AND PROCESSING

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.15%. Typical conditions with a desiccant drier: temperature 80 ° C, dew point -20 ° C or below, time 2-4 h or more. Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

Injection Molding Processing Parameters

Melt Temperature  
240 - 260°C

Mold Temperature  
40 - 60°C

Injection Speed  
medium

## PRODUCT SAFETY AND APPROVALS

For safety instruction please refer to Material Safety Data Sheet  
ROHS compliant 2011/65/EU and following amendments



# RADILON MIXLOY S RVA150 100 NT

PROPERTY	STANDARD	UNIT	VALUE		
			DAM*	Cond**	
<b>PHYSICAL PROPERTIES</b>					
Density	ISO 1183	kg/m <sup>3</sup>	1190		
Water Absorption, immersion at 23°C	ISO 62	%		5.2	
Moisture Absorption 23°C - 50%RH	ISO 62	%		1.6	
<b>MECHANICAL PROPERTIES</b>					
Tensile Modulus	ISO 527-2/1A	MPa	5400		3500
Stress at Yield	ISO 527-2/1A	MPa	100		67
Yield Strain	ISO 527-2/1A	%	3.5		7
Nominal Strain at Break	ISO 527-2/1A	%	4.5		11
Flexural Modulus	ISO 178	MPa	4400		3000
Flexural Strength	ISO 178	MPa	155		100
Charpy Impact Strength	ISO 179/1eU	kJ/m <sup>2</sup>	70		80
Charpy Notched Impact Strength	ISO 179/1eA	kJ/m <sup>2</sup>	14		
Charpy Notched Impact Strength	ISO 179/1eA	kJ/m <sup>2</sup>	11		
<b>THERMAL PROPERTIES</b>					
Melting Temperature	ISO 11357-1/-3	°C		220	

\*: DAM = Dry As Moulded state according to ISO 16396-2, \*\*: Cond = Conditioned state similar to ISO 1110

