

RADILON MIXLOY S 32HSA20K 100 NT

PRELIMINARY

DESCRIPTION

PA6/ABS blend, medium viscosity extrusion grade. Heat stabilized. Natural colour.

Suitable for parts requiring low moisture absorption and high dimensional stability. Also apt for 3D printing

ISO 1043: (PA6+ABS)

REGIONAL AVAILABILITY: North America, Europe, Asia Pacific, South and Central America, Near East/Africa

THE CHARACTERISTICS SHOWN HERE MUST BE CONSIDERED PRELIMINARY AND INDICATIVE FOR A PRODUCT AT DEVELOPMENTAL STAGE

Formerly Known As LX19268

MATERIAL HANDLING AND PROCESSING

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.10%. Typical conditions with a desiccant drier: temperature 80 ° C, dew point -20 ° C or below, time 2-4 h or more. Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

Extrusion Processing Parameter:

Rear	Center Rear	Center Front	Front	Head and Die	Melt Temp
260°C	260°C	265°C	270°C	275°C	275°C
500°F	500°F	510°F	520°F	527°F	527°F

PRODUCT SAFETY AND APPROVALS

For safety instruction please refer to Material Safety Data Sheet
ROHS compliant 2011/65/EU and following amendments



RADILON MIXLOY S 32HSA20K 100 NT

PROPERTY	STANDARD	UNIT	VALUE	
			DAM*	Cond**
PHYSICAL PROPERTIES				
Density	ISO 1183	kg/m ³	1090	
Water Absorption, immersion at 23°C	ISO 62	%		6.4
Moisture Absorption 23°C - 50%RH	ISO 62	%		2
MECHANICAL PROPERTIES				
Tensile Modulus	ISO 527-2/1A	MPa	2500	
Stress at Yield	ISO 527-2/1A	MPa	60	
Yield Strain	ISO 527-2/1A	%	4	
Nominal Strain at Break	ISO 527-2/1A	%	>50	
Flexural Modulus	ISO 178	MPa	2500	
Flexural Strength	ISO 178	MPa	90	
Charpy Impact Strength	ISO 179/1eU	kJ/m ²		N
Charpy Notched Impact Strength	ISO 179/1eA	kJ/m ²		9
THERMAL PROPERTIES				
Melting Temperature	ISO 11357-1/-3	°C	220	
Vicat Softening Temperature	ISO 306	°C	130	

*: DAM = Dry As Moulded state according to ISO 16396-2, **: Cond = Conditioned state similar to ISO 1110

