

RENYCLE S GF3503UK 3050 BK

PROVISIONAL

DESCRIPTION

Partially recycled PA6, 35% glass-fibre-reinforced injection moulding grade. Improved UV resistance for outdoor exposure. Black colour.

The recycled material has been developed to reduce its environmental impact in comparison to traditional virgin options. Suitable for parts requiring high stiffness and good mechanical resistance.

ISO 1043: PA6-GF35

REGIONAL AVAILABILITY: Europe

THE CHARACTERISTICS SHOWN HERE ARE PROVISIONAL AND REFLECT THE AVERAGE VALUES OF PROPERTIES MEASURED OVER A LIMITED NUMBER OF PRODUCTION CAMPAIGNS

MATERIAL HANDLING AND PROCESSING

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.15%. Typical conditions with a desiccant drier: temperature 80 ° C, dew point -20 ° C or below, time 2-4 h or more. Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

Injection Molding Processing Parameters

Melt Temperature
240 - 280°C

Mold Temperature
80 - 90°C

Injection Speed
medium-high

PRODUCT SAFETY AND APPROVALS

For safety instruction please refer to Material Safety Data Sheet
ROHS compliant 2011/65/EU and following amendments



RENYCLE S GF3503UK 3050 BK

PROPERTY	STANDARD	UNIT	VALUE	
			DAM*	Cond**
PHYSICAL PROPERTIES				
Density	ISO 1183	kg/m ³	1420	
Melt Flow Rate	ISO 1133	g/10min		5
Moulding shrinkage - Parallel / Normal	ISO 294-4	%	0.3 / 0.8	
Water Absorption, immersion at 23°C	ISO 62	%		6.4
Moisture Absorption 23°C - 50%RH	ISO 62	%		1.8
MECHANICAL PROPERTIES				
Tensile Modulus	ISO 527-2/1A	MPa	10500	
Stress at Break	ISO 527-2/1A	MPa	155	
Strain at Break	ISO 527-2/1A	%	2.7	
Flexural Modulus	ISO 178	MPa	10300	
Flexural Strength	ISO 178	MPa	245	
Charpy Impact Strength	ISO 179/1eU	kJ/m ²	75	
Charpy Notched Impact Strength	ISO 179/1eA	kJ/m ²	11	
THERMAL PROPERTIES				
Melting Temperature	ISO 11357-1/-3	°C	215	

*: DAM = Dry As Moulded state according to ISO 16396-2, **: Cond = Conditioned state similar to ISO 1110

1: Temperature [°C] / Load [kg]

2: Melt Temperature [°C] / Mold Temperature [°C] / Cavity Pressure [MPa]

