



# Technical Data Sheet

Product Name  
**SCGC™ HDPE**

Product Type

**High Density Polyethylene**

Product Grade  
**SX002J**

## Product Description

SCGC™ HDPE SX002J is a high density polyethylene resin with superior stress cracking resistant and excellent mechanical property balance. It is particularly designed for light-weight carbonated soft drink caps. This resin has excellent processability for both injection molding and continuous compression molding.

## Typical Application

- Beverage caps and closures
- Carbonated soft drink
- Sparkling water

## Product Characteristics

- Superior ESCR
- Excellent balance of stiffness and toughness
- Good organoleptic property
- Contain Slip agent for good removal torque

## International Compliance

- US FDA 21 CFR 177.1520
- Regulation (EU) no. 10/2011

## Physical Properties

Properties	Test Method	Typical Value	Unit
Melt Flow Rate at 190 °C and 2.16 kg	ISO 1133	0.55	g/10 min
Density	ISO 1183-2	0.955	g/cm <sup>3</sup>
Tensile Modulus (1B, 1mm/min)	ISO 527	1,000	MPa
Tensile Strength at Yield (1B, 50 mm/min)	ISO 527	25	MPa
Tensile strength at Break (1B, 50 mm/min)	ISO 527	16	MPa
Elongation at Yield	ISO 527	11	%
Flexural Modulus	ISO 178	1,100	MPa
Charpy impact strength at 23 °C	ISO 179	8	kJ/m <sup>2</sup>
Environmental Stress Cracking Resistance (ESCR), F50, conditionB, 10% Igepal	ASTM D 1693	> 1,000	hrs
Melting Point	ASTM D 2117	130	°C
HDT at 4.6 kg/cm <sup>2</sup>	ASTM D 648	70	°C

**Note:** • The given values are typical value measured on the product. Values herein are not to be constructed as a product specification.

Thai Polyethylene Co., Ltd.





<b>Technical Data Sheet</b>		Product Name <b>SCGC™ HDPE</b>
Product Type	<b>High Density Polyethylene</b>	Product Grade <b>SX002J</b>

### Processing Guidelines

The actual processing condition depends on each machine type, product size and mold design. Generally, melt temperature should be 210-240°C for injection molding and 160-200°C for continuous compression molding. The exceed melt temperature than 250°C might affect organoleptic property

### Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products, contact your SCG Chemicals technical services at the address as specified below.

### Product Available Form

- Pellet

### Product Packaging

- 25 kg loose bag
- 25 kg stretch wrap palletized
- 750 kg big bag
- Sea bulk container

### Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Co., Ltd.
- Product(s) should be stored in dry and dust free location at temperature below 50 °C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.

Thai Polyethylene Co., Ltd.

