



Technical Data Sheet

Product Type

Polyethylene for Rotational Moulding

Product Name

SCGC™ LLDPE

Product Grade

M40

Product Description

SCGC M40 series are color compound linear-low density polyethylene (LLDPE) for rotational moulding applications. These grades are suitable for containers and general applications which have wall thickness less than 5 mm. M40 is designed for outdoor application with UV8 rating.

Typical Application

- Cooler boxes
- Portable containers
- Material handling containers
- General purpose moulding
- Fish bins

Product Characteristics

- High impact strength
- Low shrinkage and warpage
- Consistent dimension

International Compliance

- Base resin of M40 series meets the requirements of U.S. Food and Drug Administration (FDA) 21 CFR Part 177.1520 Olefin polymers (c) 2.1 for food contact under conditions of use D-G (21 CFR 176.170(c) Table 2), for all food types.
- For compliance of specific colors, please contact our technical services.

Physical Properties

Properties	Test Method	Typical Value	Unit
Melt Flow Rate @ 190°C, 2.16 kg	ASTM D 1238	4.0	g/10 min
Density	ASTM D 1505	0.932	g/cm ³
Melting Point	ASTM D 2117	125 (257)	°C (°F)
Crystallization Point	ASTM D 2117	110 (230)	°C (°F)
Heat Deflection Temperature @ 0.455 MPa	ASTM D 648	58 (136)	°C (°F)
Vicat Softening Temperature	ASTM D 1525	108 (226)	°C (°F)
Mechanical Properties			
Tensile Strength at Yield @ Speed 50 mm/min	ASTM D 638	17 (2500)	MPa (psi)
Tensile Strength at Break @ Speed 50 mm/min	ASTM D 638	25 (3600)	MPa (psi)
Elongation at Break @ Speed 50 mm/min	ASTM D 638	1000	%
Flexural Modulus	ASTM D 790	570 (82700)	MPa (psi)
Surface Hardness	ASTM D 2240	55	Shore D
ARM Impact Strength @ -40°C (5.5 mm rotomolded sample)	ARM Method	28 (114)	J/mm (lb-ft)
Brittleness Temperature	ASTM D 746	< -60 (-76)	°C (°F)

Note: • The given values are typical value measured on the product. Values herein are not to be constructed as a product specification.

Thai Polyethylene Co., Ltd.





Technical Data Sheet		Product Name SCGC™ LLDPE
Product Type Polyethylene for Rotational Moulding		Product Grade M40

Processing Guidelines

Moulding cycles depend on mould materials and its wall thickness, oven temperature, and shot size. Typical oven temperatures should be set between 250 and 300°C. The recommended PIAT is about 190 °C for M40. The optimum PIAT may vary with a color shade.

Points of Concerns

- It is not recommended to flame the surfaces of molded parts with an open torch due to risk of thermal degradation and premature failure.
- Inclusion of fillers or recycled materials into the resins either by compounding or dry blending is not recommended due to risk of compromised impact strength.
- Use of pigments above 0.3% by dry blending into natural powder should be avoided due to risks of lower impact strength.
- Additional antioxidants, internal lubricants, or UV stabilizers into the virgin resins during the compounding process should be considered depending on the end applications.
- The discoloration to the products may be occurred, irrespective of period of time, due to external factors such as gas fading, staining, sublimation, migration, contamination with packaging or chemicals in contact, either directly or indirectly.
- Customer shall be responsible for testing, verification, and approval of final products for fit-for-use in terms of the customer's own use and end user's use both functions and appearance before make warranties of merchantability.

Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products, contact your SCG Chemicals technical services at the address as specified below.

Product Available Form

- Color compound powder

Product Packaging

- 25 kg loose bag
- 25 kg stretch wrap palletized

Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Co., Ltd.
- Product(s) should be stored in dry and dust free location at temperature below 50 °C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.

Thai Polyethylene Co., Ltd.

