



Technical Data Sheet

Product Name

SCGC™ LLDPE

Product Type

Polyethylene from Post-Consumer Recycled Resin

Product Grade

PCRLB02P

Product Description

SCGC PCRLB02P contains 57% post-consumer recycled polyethylene for rotational molding applications. It is available in natural color PCR resin, translucent light brown color, which provided in pellet (PCRLB02) and powder form (PCRLB02P). The product exhibits high melt flow rate and balance of impact strength, stiffness, and processability. It is suitable for furniture, decorative items, and other general purpose articles. The post-consumer recycled resin, PCRLB02, exhibits a carbon footprint of 1.20 kilograms of CO₂ equivalent per kilogram of product⁽¹⁾.

Typical Application

- Furniture
- Decorative items
- General purpose articles

Product Characteristics

- Suitable for rotational molding
- High PCR content with natural color
- Smooth surface with less pinhole
- Good impact strength
- UV-stabilized (UV8) for outdoor use

International Compliance

- Made from PCR material that complies with the Global Recycled Standard (GRS).

Physical Properties

Property	Test Method	Typical Value	Unit
Resin Properties			
Melt Flow Rate	ASTM D 1238 @ 190 °C, 2.16 kg	4.0	g/10 min
Density	ASTM D 1505	0.933	g/cm ³
Heat Deflection Temperature	ASTM D 648 @ 0.455 MPa	54 (129)	°C (°F)
Vicat Softening Temperature	ASTM D 1525	108 (226)	°C (°F)
Mechanical Properties			
Tensile Strength-at-Yield	ASTM D 638 @ Speed 50 mm/min	16 (2321)	MPa (psi)
Tensile Strength-at-Break	ASTM D 638 @ Speed 50 mm/min	21 (3046)	MPa (psi)
Elongation-at-Break	ASTM D 638 @ Speed 50 mm/min	900	%
Flexural Modulus	ASTM D 790	734 (106458)	MPa (psi)
Surface Hardness	ASTM D 2240	56	Shore D
ARM Impact Strength @ -40 °C	ARM Method (5.5 mm rotomoulded sample)	17 (69)	J/mm (lb-ft)

Note:

the given values are typical values measured on the product. Values herein are not to be constructed as a product specification.

(1) Carbon footprint value is self-calculated using polymer formula.

SCGC ICO Polymers Co., Ltd.





Technical Data Sheet

Product Name

SCGC™ LLDPE

Product Type

Polyethylene from Post-Consumer Recycled Resin

Product Grade

PCRLB02P

Processing Guidelines

Moulding cycles depend on mould materials and its wall thickness, oven temperature, and shot size. Typical oven temperatures should be set between 250 and 300 °C. The recommended PIAT for PCRLB02P are about 230 °C.

Points of Concerns

- It is not recommended to flame the surfaces of molded parts with an open torch due to risk of thermal degradation and premature failure.
- Inclusion of fillers or recycled materials into the resins either by compounding or dry blending is not recommended due to risk of compromised impact strength.
- Use of pigments above 0.3% by dry blending into natural powder should be avoided due to risks of lower impact strength.
- Additional antioxidants, internal lubricants, or UV stabilizers into the virgin resins during the compounding process should be considered depending on the end applications.
- For black compound, use up the powder as quickly as possible after the package is opened due to a high moisture pick-up that will result to pinholing and poor impact strength.

Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products, please contact your SCG Chemicals technical services at the address as specified below.

Product Available Forms

- Natural pellet (PCRLB02)
- Natural powder (PCRLB02P)

Product Packaging

- 25 kg loose bag
- 25 kg stretch wrap palletized

Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Company Limited / Thai Polypropylene Company Limited / SCGC ICO Polymers Company Limited.
- Product(s) should be stored in dry and dust free location at temperature below 50 °C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be sloped.

SCGC ICO Polymers Co., Ltd.

