



# TECHNICAL DATA SHEET

Product Name

**SCG PP**

Product Type

**Polypropylene Impact Copolymer for Caps and Closures**

Product Grade

**P443J**

## Product Description

SCG PP P443J is an impact copolymer polypropylene resin with good processability and good mechanical property. It is particularly designed for injection molding and continuous compression molding of caps and closures for the packaging beverages

## Typical Application

- Beverage caps and closures
- Carbonated soft drink
  - Hot-filled beverage

## Product Characteristics

- Good processability
- High stiffness
- High heat resistance
- With slip agent for good opening torque

## International Compliance

- US FDA 21 CFR 177.1520
- Commission Regulation (EU) no. 10/2011

**Note:** Direct food contact is subjected to the extraction provisions of the regulation on the finished food contact package

## Physical Properties

Property	Test Method	Typical Value	Unit
Melt Flow Rate	ASTM D 1238 @ 230°C, 2.16 kg	6.0	g/10 min
Density	ASTM D 1505	0.910	g/cm <sup>3</sup>
Tensile Strength at Yield	ASTM D 638 @ Crosshead speed 50 mm/min	290	kg/cm <sup>2</sup>
Tensile Strength at Break	ASTM D 638 @ Crosshead speed 50 mm/min	200	kg/cm <sup>2</sup>
Elongation at Break	ASTM D 638 @ Crosshead speed 50 mm/min	130	%
Flexural Modulus	ASTM D 790	15,000	kg/cm <sup>2</sup>
Notched Izod Impact Strength	ASTM D 256 @ 23°C	108	J/m
Notched Izod Impact Strength	ASTM D 256 @ 0°C	78	J/m
Rockwell Hardness	ASTM D 785	66	R-Scale
Melting Point	ASTM D 2117	165	°C
Heat Deflection Temperature (HDT)	ASTM D 648 @ 4.6 kg/cm <sup>2</sup>	120	°C
% Shrinkage (2 mm) MD	TPE Method	1.30	%
% Shrinkage (2 mm) TD	TPE Method	1.30	%

SCG Performance Chemicals Co., Ltd.





## TECHNICAL DATA SHEET

Product Name

**SCG PP**

Product Type

**Polypropylene Impact Copolymer for Caps and Closures**

Product Grade

**P443J**

**Note:** the given values are typical value measured on the product. Values herein are not to be constructed as a product specification.

### Processing Guidelines

The actual processing condition depends on each machine type, product size, and mold design. Generally, melt temperature should be 230-250°C for injection molding and 180-210°C for continuous compression molding. The exceed melt temperature than 250°C might affect organoleptic property.

### Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products contact your SCG Chemicals technical service at the address or telephone number as specified below.

### Product Available Form

- Pellet

### Product Packaging

- 25 kg loose bag
- 25 kg stretch wrap palletized
- 750 kg big bag
- Seabulk container

### Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Company Limited/ Thai Polypropylene Company Limited.
- Product(s) should be stored in dry and dust free location at temperature below 50°C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabeled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.

SCG Performance Chemicals Co., Ltd.

