



TECHNICAL DATA SHEET

Product Type

Polypropylene Impact Copolymer

Product Name

SCG PP

Product Grade

P483JU

Product Description

SCG PP P483JU is a developmental of high stiffness polypropylene impact copolymer product which contains anti-static agent and UV stabilizer. It is designed for very high stiffness, creep resistance, and high heat resistance while maintain a good impact strength than those of general impact copolymer polypropylene and suitable for injection molding application.

Typical Application

- Returnable transport packaging such as Pallet, Crate and Container
- Automotive parts
- Electrical appliance parts
- Any parts require outdoor uses agent

Product Characteristic

- Excellent stiffness
- High impact strength
- Good processibility
- Good dimension stability
- High heat resistance
- Good UV resistance
- Contained anti-static agent

International Compliance

- RoHS Directive 2011/65/EU
- REACH Regulation (EC) 1907/2006

Physical Properties

Property	Test Method	Typical Value	Unit
Melt Flow Rate	ASTM D 1238 @ 230 °C, 2.16 kg	5	g/10 min
Density	ASTM D 1505	0.91	g/cm ³
Tensile Strength at Yield	ASTM D 638 @ Crosshead speed 50 mm/min	300	kg/cm ²
Flexural Modulus	ASTM D 790	16,500	kg/cm ²
Notched Izod Impact	ASTM D 256 @ 23°C	108	J/m
Notched Izod Impact	ASTM D 256 @ 0°C	69	J/m
Notched Izod Impact	ASTM D 256 @ -20°C	59	J/m
Melting Point	ASTM D 2117	166	°C
Heat Deflection Temperature (HDT)	ASTM D 648 @ 4.6 kg/cm ²	125	°C

Note:

- Conversion factor for changing unit from kg/cm² to MPa is divided by 10.20
- The given values are typical value measured on the product. Values herein are not to be constructed as a product specification.

Processing Guidelines

The actual processing conditions depend on each machine type, product size, mold design and environment.

Recommended processing conditions:

Melt temperature: 210-250°C

Mold temperature: 25-70°C

Injection speed: Fast

Screw speed 40-70 rpm

Pressure: Injection 40-80%

Packing and Holding 30-60%

Back 10% of Max Pressure

SCG Plastics Co., Ltd.





TECHNICAL DATA SHEET

Product Type

Polypropylene Impact Copolymer

Product Name

SCG PP

Product Grade

P483JU

Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products contact your SCG Chemicals technical service at the address or telephone number as specified below.

Product Available Form

- Block pellet

Product Packaging

- 25 kg loose bag
- 25 kg stretch wrap palletized
- 750 kg big bag
- Seabulk container
- 750 kg big bag

Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Company Limited.
- Product(s) should be stored in dry and dust free location at temperature below 50°C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.

SCG Plastics Co., Ltd.

