



TECHNICAL DATA SHEET

Product Name

SCG PP

Product Type

Polypropylene Impact Copolymer

Product Grade

P722JO

Product Description

SCG PP P722JO is an impact copolymer polypropylene resin which contains UV stabilizer. This resin is recommended for producing battery case from injection molding process.

Typical Application

- Automotive battery case
- Industrial uses

Product Characteristics

- High impact strength and stiffness
- Good processability
- Good dimensional stability
- Good UV resistance

International

- Directive 94/62/EC on PPWD
- Coalition of Northeastern Governors (CONEG)
- Directive 2002/95/EC (RoHS1)
- Directive (EU) 2015/863 amending annex II to Directive 2011/65/EU (RoHS2)
- Directive 2000/53/EC on ELV
- REACH Regulation (EC) No 1907/2006

Physical Properties

Property	Test Method	Typical Value	Unit
Melt Flow Rate	ASTM D 1238 @ 230°C, 2.16 kg	10	g/10 min
Density	ASTM D 1505	0.910	g/cm ³
Tensile Strength at Yield	ASTM D 638 @ Speed 50 mm/min	300	kg/cm ²
Tensile Strength at Break	ASTM D 638 @ Speed 50 mm/min	180	kg/cm ²
Flexural Modulus	ASTM D 790	13,000	kg/cm ²
Notched Izod Impact	ASTM D 256 @ 23°C	98	J/m
Notched Izod Impact	ASTM D 256 @ 0°C	59	J/m
Notched Izod Impact	ASTM D 256 @ -20°C	49	J/m
Rockwell Hardness	ASTM D 785	75	°C
Heat Deflection Temperature	ASTM D 648 @ 4.6 kg/cm ²	120	°C
Flammability	UL-94	HB	-

Note: the given values are typical value measured on the product. Values herein are not to be constructed as a product specification.

SCG Performance Chemicals Co., Ltd.





TECHNICAL DATA SHEET

Product Name

SCG PP

Product Type

Polypropylene Impact Copolymer

Product Grade

P722JO

Processing

The actual processing condition depends on each machine type, product size, and mold design. Generally, melt temperature should be 230-270°C for injection molding. The exceed melt temperature than 300°C might effect on color or appearance of product.

Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products contact your SCG Chemicals technical service at the address or telephone number as specified below.

Product Available Form

- Pellet

Product Packaging

- 25 kg loose bag
- 25 kg stretch wrap palletized
- 750 kg big bag
- Seabulk container
- 750 kg big bag

Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Company Limited/ Thai Polypropylene Company Limited.
- Product(s) should be stored in dry and dust free location at temperature below 50°C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.

SCG Performance Chemicals Co., Ltd.

