



# TECHNICAL DATA SHEET

Product Name

**SCG PP**

Product Type

**Polypropylene Impact Copolymer**

Product Grade

**P441JU**

## Product Description

SCG PP P441JU is an impact co-polypropylene resin which contains anti-static agent and UV stabilizer. It is designed for injection molding process. This resin is recommended for product that requires good outdoor performance.

## Typical Application

- Pail, Crates, Industrial uses
- Automotive parts
- Electrical appliance parts
- Furniture
- Containers

## Product Characteristics

- High impact strength
- Good processibility and stiffness
- Good UV resistance

## International

- U.S FDA 21 CFR 177.1520
- UL Yellow Card E202743
- RoHS Directive 2011/65/EU

## Physical Properties

Property	Test Method	Typical Value	Unit
Melt Flow Rate	ASTM D 1238 @ 230°C, 2.16 kg	5	g/10 min
Density	ASTM D 1505	0.910	g/cm <sup>3</sup>
Tensile Strength at Yield	ASTM D 638 @ speed 50 mm/min	270	kg/cm <sup>2</sup>
Tensile Strength at Break	ASTM D 638 @ speed 50 mm/min	200	kg/cm <sup>2</sup>
Flexural Modulus	ASTM D 790	12,500	kg/cm <sup>2</sup>
Notched Izod Impact	ASTM D 256 @ 23°C	118	J/m
Notched Izod Impact	ASTM D 256 @ 0°C	65	J/m
Notched Izod Impact	ASTM D 256 @ -20°C	49	J/m
Rockwell Hardness	ASTM D 785	60	R-Scale
Melting Point	ASTM D 2117	163	°C
Vicat Softening Point	ASTM D 1525	150	°C
Heat Deflection Temperature (HDT)	ASTM D 648 @ 4.6 kg/cm <sup>2</sup>	100	°C
% Shrinkage (2mmt) MD	TPE Method	1.2	%
TD	TPE Method	1.1	%
Flammability	UL - 94	HB	-

**Note:** the given values are typical values measured on the product. Values herein are not to be constructed as a product specification.

SCG Plastics Co., Ltd. / SCG Performance Chemicals Co., Ltd.





## TECHNICAL DATA SHEET

Product Name

**SCG PP**

Product Type

**Polypropylene Impact Copolymer**

Product Grade

**P441JU**

### Processing Guidelines

The actual processing conditions depend on each machine type, product size, mold design and environment.

Recommended processing conditions:

Melt temperature: 230-270°C

Mold temperature: 25-70°C

Injection speed: Fast

Pressure (of Max. Pressure):

Injection 40-80%

Packing and Holding 30-60%

Back 10%

### Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products contact your SCG Chemicals technical service at the address or telephone number as specified below.

### Product Available Form

- Block pellet

### Product Packaging

- 25 kg loose bag
- 25 kg stretch wrap palletized
- 750 kg big bag
- Seabulk container

### Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Company Limited/ Thai Polypropylene Company Limited.
- Product(s) should be stored in dry and dust free location at temperature below 50°C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.

SCG Plastics Co., Ltd. / SCG Performance Chemicals Co., Ltd.

