



Technical Data Sheet

Product Name
SCGC™ PP

Product Type
Polypropylene Resin

Product Grade
P400S

Product Description

SCGC™ PP P400S is a homopolymer polypropylene resin which is specially designed for flat yarn or raffia products and monofilament application as well. SCGC™ PP P400S offers good features for Flat Yarn application as consistency process ability, high productivity with balance good mechanical properties.

Typical Application

- Woven bags
- Flexible Intermediate Bulk Containers
- Ropes & twines
- Sheet
- Stap
- Straw

Product Characteristics

- Good process ability
- High productivity
- Good mechanical properties
- Food contact applicable

International Compliance

- U.S. FDA 21 CFR 177.1520
- Regulation (EU) No.10/2011
- REACH Regulation (EC) No.1907/2006
- RoHS Direction 2011/65/EU

Physical Properties

Properties	Test Method	Typical Value	Unit
Melt Flow Rate	ASTM D 1238 @ 230 °C, 2.16 kg	3.5	g/10 min
Density	ASTM D 1505	0.91	g/cm ³
Melting Point	ASTM D 2117	163	°C
Vicat Softening Point	ASTM D 1525	155	°C
Heat Deflection Temperature (HDT)	ASTM D 648 @ 4.6 kg/cm ²	110	°C
Tensile Strength at Yield	ASTM D 638	350	kg/cm ²
Tensile Strength at Break	ASTM D 638	230	kg/cm ²
Elongation at Break	ASTM D 638	650	%
Flexural Modulus	ASTM D 790	15,500	kg/cm ²
Notched Izod Impact	ASTM D 256 @ 23 °C	40	J/m
Haze	ASTM D 1003	50	%
Gloss	ASTM D 2457	65	%

Note:

- Conversion factor for changing unit from kg/cm² to MPa is divided by 10.20.
- There results above are under SCGC's condition and method from specific sample, should be not used for representative to lot product qualities.

Thai Polyethylene Co., Ltd.





Technical Data Sheet		Product Name SCGC™ PP
Product Type Polypropylene Resin	Product Grade P400S	

Processing Guidelines

Recommended processing conditions:

Flat yarn: Processing temperature around 190 – 260 °C, Stretching Temperature 140 – 160 °C, Stretching Ratio 5 - 7

Monofilament: Processing temperature around 250 – 280 °C, Stretching Temperature 95 – 105 °C, Stretching Ratio 8 – 12

However, these conditions are only guideline for actual processing conditions should be adjusted case by case because it depends on machine type, screw configuration, product design and environment.

Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products, contact your SCG Chemicals technical services at the address as specified below.

Product Available Form

- Pellet

Product Packaging

- 25 kg loose bag
- 25 kg stretch wrap palletized
- 750 kg big bag
- Sea bulk container

Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Company Limited.
- Product(s) should be stored in dry and dust free location at temperature below 50 °C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.

Thai Polyethylene Co., Ltd.

