



Technical Data Sheet

Product Name
SCGC™ PP

Product Type
Polypropylene Copolymer Resin

Product Grade
P722JO

Product Description

SCGC™ PP P722JO is polypropylene impact copolymer which contains UV stabilizer. This resin is recommended for producing battery case from injection molding process.

Typical Application

- Automotive battery case
- Industrial uses

Product Characteristics

- High impact strength and stiffness
- Good processability
- Good dimensional stability
- Good UV resistance

International Compliance

- Directive 94/62/EC on PPWD
- Coalition of Northeastern Governors (CONEG)
- RoHS Directive 2011/65/EU
- Directive 2000/53/EC on ELV
- REACH Regulation (EC) No. 1907/2006

Physical Properties

Properties	Test Method	Typical Value	Unit
Melt Flow Rate	ASTM D 1238 @ 230 °C, 2.16 kg	10	g/ 10 min
Density	ASTM D 1505	0.910	g/cm ³
Heat Deflection Temperature (HDT)	ASTM D 648 @ 4.6 kg/cm ²	120	°C
Tensile Strength at Yield	ASTM D 638 @ Speed 50 mm/min	300	kg/cm ²
Tensile Strength at Break	ASTM D 638 @ Speed 50 mm/min	180	kg/cm ²
Flexural Modulus	ASTM D 790	13,000	kg/cm ²
Notched Izod Impact	ASTM D 256 @ 23 °C	98	J/m
Notched Izod Impact	ASTM D 256 @ 0 °C	59	J/m
Notched Izod Impact	ASTM D 256 @ -20 °C	49	J/m
Rockwell Hardness	ASTM D 785	75	R-Scale
Flammability	UL-94	HB	-

Note: - The given values are typical value measured on the product. Values herein are not to be constructed as a product specification.
- Conversion factor for changing unit from kg/cm² to MPa is divided by 10.20.

Thai Polyethylene Co., Ltd.





Technical Data Sheet	Product Name SCGC™ PP
Product Type Polypropylene Copolymer Resin	Product Grade P722JO

Processing Guidelines

The actual processing conditions depend on each machine type, product size, mold design and environment.

Recommended processing conditions:

Melt temperature: 210-250 °C

Mold temperature: 25-70 °C

Injection speed: Fast

Screw speed: 40-70 rpm

Pressure: Injection: 40-80 %

Packing and Holding: 30-60%

Back: 10% of Max Pressure

Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products, contact your SCG Chemicals technical services at the address as specified below.

Product Available Form

- Pellet

Product Packaging

- 25 kg loose bag
- 25 kg stretch wrap palletized
- 750 kg big bag
- Sea bulk container

Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Company Limited.
- Product(s) should be stored in dry and dust free location at temperature below 50 °C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.

Thai Polyethylene Co., Ltd.

