



Technical Data Sheet

Product Name
SCGC™ PP

Product Type
Polypropylene Resin

Product Grade
P483JU

Product Description

SCGC™ PP P483JU is a developmental of high stiffness polypropylene impact copolymer product which contains anti-static agent and UV stabilizer. It is designed for very high stiffness, creep resistance, and high heat resistance while maintain a good impact strength than those of general polypropylene impact copolymer. It is suitable for injection molding process.

Typical Application

- Returnable transport packaging such as Pallet, Crate, and Container
- Automotive parts
- Electrical appliance parts
- Any parts require outdoor uses agent

Product Characteristics

- Excellent stiffness
- High impact strength
- Good process ability
- Good dimension stability
- High heat resistance
- Good UV resistance

International Compliance

- RoHS Directive 2011/65/EU (RoHS 2)
- REACH Regulation (EC) No. 1907/2006
- Directive 94/62/EC

Physical Properties

Properties	Test Method	Typical Value	Unit
Melt Flow Rate	ASTM D 1238 @ 230 °C, 2.16 kg	5	g/ 10 min
Density	ASTM D 1505	0.91	g/cm ³
Melting Point	ASTM D 2117	166	°C
Heat Deflection Temperature (HDT)	ASTM D 648 @ 4.6 kg/cm ²	125	°C
Tensile Strength at Yield	ASTM D 638 @ Speed 50 mm/min	300	kg/cm ²
Flexural Modulus	ASTM D 790	16,500	kg/cm ²
Notched Izod Impact Resistance	ASTM D 256 @ 23 °C	108	J/m
Notched Izod Impact Resistance	ASTM D 256 @ 0 °C	69	J/m
Notched Izod Impact Resistance	ASTM D 256 @ -20 °C	59	J/m

Note: - The given values are typical value measured on the product. Values herein are not to be constructed as a product specification.
- Conversion factor for changing unit from kg/cm² to MPa is divided by 10.20.

Thai Polyethylene Co., Ltd.





Technical Data Sheet	Product Name SCGC™ PP
Product Type Polypropylene Resin	Product Grade P483JU

Processing Guidelines

The actual processing conditions depend on each machine type, product size, mold design and environment.

Recommended processing conditions:

Melt temperature: 210-250 °C Mold temperature: 25-70 °C Injection speed: Fast Screw speed: 40-70 rpm
Pressure: Injection: 40-80 % Packing and Holding: 30 -60% Back: 10% of Max Pressure

Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products, contact your SCG Chemicals technical services at the address as specified below.

Product Available Form

- Pellet

Product Packaging

- 25 kg loose bag
- 25 kg stretch wrap palletized
- 750 kg big bag
- Sea bulk container

Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Company Limited.
- Product(s) should be stored in dry and dust free location at temperature below 50 °C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.

Thai Polyethylene Co., Ltd.

