



Technical Data Sheet

Product Name
SCGC™ PP

Product Type

Polypropylene Copolymer Resin

Product Grade

P341S

Product Description

SCGC PP, P341S is a development grade of impact copolymer polypropylene with low flowability. It exhibits excellent impact resistance and maintain stiffness designed for automotive parts, general purpose products and thermoforming packaging. It is suitable for extrusion and thermoforming.

Typical Application

- Corrugated extruded board
- Thermoforming packaging
- Automotive parts

Product Characteristics

- Superior impact strength
- Balance stiffness
- Good dimension stability

International Compliance

- U.S. FDA 21 CFR 177.1520

Physical Properties

Properties	Test Method	Typical Value	Unit
Melt Flow Rate	ASTM D 1238 @ 230°C, 2.16 kg	1.8	g/10 min
Density	ASTM D 1505	0.910	g/cm ³
Flexural Modulus	ASTM D 790	12,000	kg/cm ²
Notched Izod Impact	ASTM D 256 @ 23°C	No break	J/m
Notched Izod Impact	ASTM D 256 @ 0°C	100	J/m
Notched Izod Impact	ASTM D 256 @ -20°C	70	J/m
Tensile strength at Yield	ASTM D 638 @ speed 50 mm/min	250	kg/cm ²
Heat Deflection Temperature (HDT)	ASTM D 648 @ 4.6 kg/cm ²	100	°C

Note: - The given values are typical value measured on the product. Values herein are not to be constructed as a product specification.
- Conversion factor for changing unit from kg/cm² to MPa is divided by 10.20.

Thai Polyethylene Co., Ltd.





Technical Data Sheet

Product Name
SCGC™ PP

Product Type

Polypropylene Copolymer Resin

Product Grade

P341S

Processing Guidelines

The actual processing conditions depend on each machine type, product size, mold design and environment. Recommended processing temperature is around 200-250°C. The heating temperature of thermoforming process depend on machine and line speed. Recommended temperature on sheet before forming should be around 155-160°C.

Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products, contact your SCG Chemicals technical service at the address or telephone number as specified below.

Product Available Form

- Pellet

Product Packaging

- 25 kg loose bag
- 25 kg stretch wrap palletized
- 750 kg big bag
- Sea bulk container

Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Company Limited.
- Product(s) should be stored in dry and dust free location at temperature below 50 °C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.

Thai Polyethylene Co., Ltd.

