



Technical Data Sheet

Product Name
SCGC™ PP

Product Type

Polypropylene Resin

Product Grade
P809JM

Product Description

SCGC PP P809JM is a homopolymer polypropylene resin that is well-suited to healthcare and pharmaceutical products. P809JM exhibits high flow ability, high clarity and is compliant to FDA and USP requirements. P809JM can be injection molded and sterilized by ethylene oxide.

Typical Application

- Syringe barrel and plunger
- Lab wares
- Applications required high transparency and stiffness

Product Characteristics

- High transparency
- High stiffness
- Easy processing

International Compliance

- Food contact applicable (Complies with U.S. FDA 21 CFR 177.1520)
- Complies with USP class VI

Notice : It is strongly recommended that all potential activities for applications related to pharmaceutical, medical device, laboratory and diagnostics area have to be discussed with technical services department first. It is responsibility of customers to determine that the product is safe, lawful and technically suitable for the intended use. Thai Polyethylene Company Limited/Thai Polypropylene Company Limited makes no warranties concerning the suitability of SCG Chemicals' product for using in any given medical application.

Physical Properties

Properties	Test Method	Typical Value	Unit
Melt Flow Rate	ASTM D 1238 @ 230 °C, 2.16 kg	30	g/10 min
Density	ASTM D 1505	0.910	g/cm ³
Tensile Strength at Break	ASTM D 638 @ Crosshead speed 50 mm/min	380	kg/cm ²
Elongation at Break	ASTM D 638 @ Crosshead speed 50 mm/min	8	%
Flexural Modulus	ASTM D 790	19,000	kg/cm ²
Notched Izod Impact Strength	ASTM D 256 @ 23 °C	30	J/m
Rockwell Hardness	ASTM D 785	90	R-Scale
Melting Point	ASTM D 2117	163	°C
Vicat Softening Point	ASTM D 1525	155	°C
Heat Deflection Temperature (HDT)	ASTM D 648 @ 4.6 kg/cm ²	132	°C
% Shrinkage (2 mm.) MD	TPE Method	1.35	%
TD	TPE Method	1.35	%

(% Shrinkage depending on wall thickness and molding parameter)

Note:

- The given values are typical value measured on the product. Values herein are not to be constructed as a product specification.
- Conversion factor for changing unit from kg/cm² to MPa is divided by 10.20.

Thai Polyethylene Co., Ltd.





Technical Data Sheet		Product Name SCGC™ PP
Product Type Polypropylene Resin	Product Grade P809JM	

Processing Guidelines

The actual processing condition depends on each machine type, product size and mold design. Generally, melt temperature should be 210-250 °C for injection molding, Mold temperature: 20-50 °C and the exceed melt temperature than 250 °C might affect organoleptic property.

Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products contact your technical services at the address as specified below.

Product Available Form

- Pellet

Product Packaging

- 25 kg loose bag
- 25 kg stretch wrap palletized

Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Company Limited.
- Product(s) should be stored in dry and dust free location at temperature below 50 °C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.

Thai Polyethylene Co., Ltd.

