



Technical Data Sheet

Product Name
SCGC™ PP

Product Type
Polypropylene Copolymer Resin

Product Grade
P765J

Product Description

P765J is very high impact polypropylene copolymer. It is designed for automotive interior and exterior parts such as door trims, instrumental panel and bumper which it's suitable for injection molding process. This resin is recommended for product that require very high impact strength at room temperature and low temperature.

Typical Application

- Automotive exterior/interior parts
- Home appliances parts
- Compounding
- Complicated industrial parts

Product Characteristics

- Excellence impact resistance
- Medium flowability

International Compliance

- RoHS Directive 2011/65/EU
- Directive 2000/53/EC on ELV
- REACH Regulation (EC) No. 1907/2006

Physical Properties

Properties	Test Method	Typical Value	Unit
Melt Flow Rate	ISO 1133 @ 230 °C, 2.16 kg	30	g/ 10 min
Density	ISO 1183	0.910	g/cm ³
Tensile Strength at Yield	ISO 527	20	MPa
Elongation at Break	ISO 527	>300	%
Flexural Modulus	ISO 178	800	MPa
Flexural Modulus	ASTM D 790	9,000	kg/cm ²
Charpy Impact Strength	ISO 179 @ 23 °C	40	kJ/m ²
Charpy Impact Strength	ISO 179 @ -20 °C	6.0	kJ/m ²
Notched Izod Impact Strength	ASTM D 256 @ 23 °C	No Break	

Note: - The given values are typical value measured on the product. Values herein are not to be constructed as a product specification.

Thai Polyethylene Co., Ltd.





Technical Data Sheet

Product Name
SCGC™ PP

Product Type
Polypropylene Copolymer Resin

Product Grade
P765J

Processing Guidelines

The actual processing conditions depend on each machine type, product size, mold design and environment.

Recommended processing conditions:

Melt temperature: 210-250 °C

Mold temperature: 25-70 °C

Injection speed: Fast

Screw speed: 40-70 rpm

Pressure: Injection: 40-80 %

Packing and Holding: 30-60%

Back: 10% of Max Pressure

Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products, contact your SCG Chemicals technical services at the address as specified below.

Product Available Form

- Pellet

Product Packaging

- 25 kg loose bag
- 25 kg stretch wrap palletized
- 750 kg big bag
- Sea bulk container

Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Company Limited.
- Product(s) should be stored in dry and dust free location at temperature below 50 °C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be sloped.

Thai Polyethylene Co., Ltd.

