



Technical Data Sheet

Product Name
SCGC™ Plastic Compound

Product Type
Thermoplastic polyolefin (TPO) compound

Product Grade
60701WHA

Product Description

60701WHA is a Thermoplastic Polyolefin (TPO) Compound. The product is designed for extrusion process in application of soft profile, gasket, seal, and etc.

Typical Application

- Extrusion process

Product Characteristics

- Excellent process ability
- Good flexibility
- Non heavy metal

International Compliance

Physical Properties

Properties	Test Method	Typical Value ¹	Unit
Specific Gravity	ASTM D 792	0.94	-
Hardness Shore A @15 sec	ASTM D 2240	69	-
Tensile strength	JIS K6723	67	kgf/cm ²
Elongation at Break	JIS K6723	887	%
Melt Flow Index (230°C, 2.16 kg)	ASTM D 1238	2.9	g/ 10 min.

Note: ¹ The above give values are typical test results which should be used as a guide only, they do not from the whole or part of a specification or guarantee.

Thai Polyethylene Co., Ltd.





Technical Data Sheet

Product Type
Thermoplastic polyolefin (TPO) compound

Product Name
SCGC™ Plastic Compound

Product Grade
60701WHA

Processing Guidelines

The actual processing condition depends on each extruder machine type, screw type and also output needed etc. Generally, temperature at extruder should be around 165-180°C as sequence from feed throat to die head. The exceed temperature than 190°C might affect to appearance, color and typical property.

Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products contact your SCG Chemicals technical services at the address as specified below.

Product Available Form

- Pellet

Product Packaging

- 20 kg Loose bag

Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Company Limited/ Thai Polypropylene Company Limited.
- Product(s) should be stored in dry and dust free location at temperature below 50°C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odor generation and color changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabeled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.

Thai Polyethylene Co., Ltd.

