

LOTADER[®] 3430

LOTADER[®] 3430 is a random ethylene-methyl acrylate-maleic anhydride terpolymer.

LOTADER[®] 3430 is a versatile adhesive for extrusion coating or lamination, designed as:

- Concentrate to be used in dry blend with LDPE. LOTADER[®] 3430 improves adhesion of LDPE on aluminium foils, metallized or primerized films.
- Ready for use resin to be used pure. LOTADER[®] 3430 gives excellent adhesion on substrates like aluminum foil, metallized plastics, paper, board, PE and some plastic films like BOPP.
- Coextrusion tie layer for PE/PA in extrusion coating process.

LOTADER[®] 3430 can also be used as a coupling agent for mineral filled compounds such as halogen free flame retardant wires and cables, a compatibiliser for polyamide/polyolefin blends and a modifier for polyamides.

Typical Properties

	Test Method	Unit	Typical Value
Methyl Acrylate Content	FTIR (internal method)	%.-wt.	15
Maleic Anhydride Content	FTIR (internal method)	%.-wt.	3.1
Melt Index (190°C/2.16kg)	ISO 1133 / ASTM D1238	g/10min.	7
Melting Point	ISO 11357-3	°C	84
Vicat Softening Temperature (10N) ¹	ISO 306 / ASTM D1525	°C	45
Density	ISO 1183 / ASTM D1505	g/cm ³	0.94
Flexural Modulus ¹	ISO 178 / ASTM D790	MPa	25
Elongation at break ¹	ISO 527-2 / ASTM D638	%	750
Tensile strength at break ¹	ISO 527-2 / ASTM D638	MPa	12
Hardness Shore D ¹	ISO 868 / ASTM D2240	-	30

¹: On compression molded samples.



Processing

LOTADER® 3430 can be extruded with standard polyolefin extrusion equipment with typical melt temperature of 270°C and up to 320°C-330°C.

LDPE purge is recommended before extruder shutdown.

Storage, Handling & Safety

LOTADER® 3430 is usually packed in waterproof bags or rigid containers with waterproof liner. It should be stored in dry conditions and be kept out of moisture in an aerated building.

Improper storage conditions may cause degradation and could have consequences on physical properties of the product. It is recommended to reseal the bag or the liner after use to protect LOTADER® 3430 against moisture.

