



益膜新

CHANG CHUN PETROCHEMICAL CO.,LTD.

EVASIN EV3851F DATA SHEET

38 mole% Ethylene Vinyl Alcohol Copolymer

Application


EV3851F with low melt flow index is a standard grade mainly designed for co-extrusion film application. This resin shows excellent balance among barrier to gases as well as processing thermal stability. This resin can also be recommended for sheet / thermoforming and shrink application.

General Property

Item	unit	Test Method	Value
Mechanical Properties			
Tensile strength at yield	MPa	ISO 527	74.4
Tensile strength at break	MPa	ISO 527	27.7
Elongation at break	%	ISO 527	19
Young's modulus	MPa	ISO 527	4000
Flexural modulus	MPa	ISO 178	3690
Flexural strength	MPa	ISO 178	112
Charpy impact strength	KJ/m ²	ISO 179-1	2.4
Rockwell hardness	HRM	ISO 2039-2	91
Density	g/cm ³	ISO 1183	1.16
Thermal Properties and Melt Characteristics			
Melting point	°C	ISO 11357	173
Crystallization point	°C	ISO 11357	151
Glass transition point	°C	ISO 11357	57
Vicat Softening Point	°C	ISO 306	162
Melt flow index	g/10min(2160g,190°C)	ISO 1133	1.8
	g/10min(2160g,210°C)	ISO 1133	3.9
Gas Barrier Properties			
O ₂ Transmission Rate at 20°C 0%RH at 20°C 65%RH at 20°C 85%RH	cm ³ .20μm/m ² .24Hrs.atm	ISO 14663-2	0.5 0.7 2
Water Vapor Transmission Rate	cm ³ .30μm/m ² .24Hrs.atm at 40°C 90%RH	ASTM E96-E	28



Melt Viscosity



Example of Processing Temperature Profile

	Barrel 1	Barrel 2	Barrel 3	Barrel 4	Barrel 5	Adapter	Die
EV3851F	175	195	205	210	215	210	210

