

Product Data

TITANPRO 7523 FOR INJECTION MOLDING

- CHARACTER** Polypropylene impact copolymer.
Titanpro 7523 is an intermediate impact material which complies with the U.S. Food and Drug Administration (FDA) regulation as specified in 21 CFR 177.1520(a)(3)(i) and (c)3.1a.
TSCA Registry: CAS# 9010-79-1
- APPLICATIONS** Automotive parts, battery casing, appliances, housewares, seating, jerrycan caps.
- ADVANTAGES** Superior balance of properties.
Good low temperature impact resistance.
Excellent heat stability.
- FABRICATION** Equipment - ram or screw injection machines.
Techniques - standard processing.

<u>TYPICAL RESIN PROPERTIES</u> ^(a)	<u>UNIT</u>	<u>7523</u>	<u>ASTM METHOD</u> ^(b)
Melt Flow Rate, at 230°C	g/10 min	4.0	D1238
Density	g/cm ³	0.9	D1505
Tensile Strength at Yield	kg/cm ²	290	D638
Elongation at Yield	%	10	D638
Flexural Modulus	kg/cm ²	13500	D790B
Notched Izod Impact Strength at 23°C	kg·cm/cm	13	D256A
Heat Deflection Temperature at 4.6 kg/cm ²	°C	85	D648
Rockwell Hardness	R scale	82	D785A
Drop weight impact at -29°C	kg.cm	280	Internal Method
Water absorption after 24 hours	%	0.02	D570

(a) Values shown are average and are not to be considered as specifications.

(b) ASTM test methods are latest under the Society's current procedures.

Shrinkage : 1.3 - 1.4% depending on the product wall thickness and molding parameters.

LOTTE CHEMICAL TITAN (M) SDN. BHD.

Titanex® • Titanlene® • Titanzex® • Titanpro® • Titanvene®

塑料专家 www.ponci.com.cn/wxb/ +13538586433 +18816996168

