

# Product Data

## TITANPRO SM840 FOR INJECTION MOLDING

<b>CHARACTER</b>	Polypropylene impact copolymer. Titanpro SM840 is an extra high flow material which complies with the U.S. Food and Drug Administration (FDA) regulation as specified in 21 CFR 177.1520(a)(3)(i) and (c)3.1a. TSCA Registry: CAS# 9010-79-1
<b>APPLICATIONS</b>	Automotive parts, appliances, housewares, washing machine tub, large flat trays, thin walled articles, flower pots, furniture.
<b>ADVANTAGES</b>	Easy processability, permitting wider latitude in design. Good toughness at low temperature. Good surface finish and color. Low molded in stresses. Excellent heat stability.
<b>FABRICATION</b>	Equipment - ram or screw injection machines. Techniques - standard processing.

<u>TYPICAL RESIN PROPERTIES</u> <sup>(a)</sup>	<u>UNIT</u>	<u>SM840</u>	<u>ASTM METHOD</u> <sup>(b)</sup>
Melt Flow Rate, at 230°C	g/10 min	<b>35</b>	D1238
Density	g/cm <sup>3</sup>	<b>0.9</b>	D1505
Tensile Strength at Yield	kg/cm <sup>2</sup>	<b>280</b>	D638
Elongation at Yield	%	<b>10</b>	D638
Flexural Modulus	kg/cm <sup>2</sup>	<b>13500</b>	D790B
Notched Izod Impact Strength at 23°C	kg·cm/cm	<b>8</b>	D256A
Heat Deflection Temperature at 4.6 kg/cm <sup>2</sup>	°C	<b>90</b>	D648
Rockwell Hardness	R scale	<b>80</b>	D785A
Drop weight impact at -29°C	kg.cm	<b>240</b>	Internal Method
Water absorption after 24 hours	%	<b>0.02</b>	D570

(a) Values shown are average and are not to be considered as specifications.

(b) ASTM test methods are latest under the Society's current procedures.

Shrinkage : 1.3 - 1.4% depending on the product wall thickness and molding parameters.

LOTTE CHEMICAL TITAN (M) SDN. BHD.

Titanex® • Titanlene® • Titanzex® • Titanpro® • Titanvene®

塑料专家 [www.ponci.com.cn/wxb/](http://www.ponci.com.cn/wxb/) +13538586433 +18816996168

