

Product Data Sheet

PT. Lotte Chemical Titan Nusantara. (Formerly known as PT TITAN Petrokimia Nusantara)

Titanvene™ LL0209SC

General Linear Low Density Film Applications

Titanvene™ LL0209SC is a linear low density polyethylene for high clarity film application. Titanvene™ LL0209SC is characterized by excellent transparency, low gel content, good process ability, and good mechanical properties with low blocking force and high slip.

Applications

Titanvene™ LL0209SC is typically used for :

- Industrial Packaging
- Food Packaging
- Transparent Film
- Shopping Bags
- Rice Bag
- Garment Sack

Recommended Processing Conditions ⁽¹⁾

Titanvene™ LL0209SC can be easily processed on normal polyethylene blow film machines at temperatures in the range of 170°C to 200°C.

Food Contact Compliance

Titanvene™ LL0209SC can be used in food contact applications. Please contact your nearest PT. Lotte Chemical TITAN Nusantara representative for more detail of food contact compliance statements for the specific grade.

General Properties	Value ⁽²⁾	Unit	Test Method
Melt Flow Rate (190°C/2.16 kg)	1.0	g/10 min	ISO 1133 Condition 4
Nominal Density	0.920	g/cm ³	ISO 1183 Method D
Vicat Softening Point	103	°C	ISO 306
Melting Point	122	°C	ISO 3146 Method C
Mechanical Properties ⁽³⁾	Value ^{(2) (4)}	Unit	Test Method
Tensile Stress at Yield	MD 11 / TD 11	MPa	ISO 1184(E) Speed I
Elongation at Break	MD 750 / TD 800	%	ISO 1184(E) Speed I
Dart Impact Strength	130	gr	ISO 7765-1 Method A
Other Properties	Value ⁽²⁾	Unit	Test Method
Clarity	70	%	ASTM D1746
Gloss	50	%	ASTM D2457
Haze	14	%	ASTM D1003
COF	0.14		BS 2782, Method 824A

(1) The optimum processing conditions can be different from one machine to the others, depend on the mould and part design.
 (2) The values shown are typical values obtained by averaging a number of tests. Small divergences from the quoted figures may occur.
 (3) Measured on 38 microns film extruded at 2:1 blow ratio.
 (4) MD = film machine direction. TD = film transversal direction.

