

Product Data

TITANPRO SM950 FOR INJECTION MOLDING

CHARACTER	Polypropylene impact copolymer. Titanpro SM950 is a nucleated extra high flow material which complies with the requirements of the U.S. Food and Drug Administration (FDA) regulation as specified in 21 CFR 177.1520(a)(3)(i) and (c)3.1a. TSCA Registry: CAS# 9010-79-1
APPLICATIONS	Automotive parts, housewares, washing machine tub and parts, large flat trays, thin walled articles.
ADVANTAGES	Easy processability, permitting wider latitude in design. Good toughness at low temperature. Good surface finish and color. Low molded in stresses and excellent heat stability.
FABRICATION	Equipment - ram or screw injection machines. Techniques - standard processing.

<u>TYPICAL RESIN PROPERTIES</u> ^(a)	<u>UNIT</u>	<u>SM950</u>	<u>ASTM METHOD</u> ^(b)
Melt Flow Rate, at 230°C	g/10 min	60	D1238
Density	g/cm ³	0.9	D1505
Tensile Strength at Yield	kg/cm ²	260	D638
Elongation at Yield	%	10	D638
Flexural Modulus	kg/cm ²	15000	D790B
Notched Izod Impact Strength at 23°C	kg·cm/cm	7	D256A
Heat Deflection Temperature at 4.6 kg/cm ²	°C	100	D648
Rockwell Hardness	R scale	80	D785A
Drop weight impact at -29°C	kg.cm	220	Internal Method
Water absorption after 24 hours	%	0.02	D570

(a) Values shown are average and are not to be considered as specifications.

(b) ASTM test methods are latest under the Society's current procedures.

Shrinkage : 1.3 - 1.4% depending on the product wall thickness and molding parameters.

LOTTE CHEMICAL TITAN (M) SDN. BHD.

Titanex® • Titanlene® • Titanzex® • Titanpro® • Titanvene®

塑料专家 www.ponci.com.cn/wxb/ +13538586433 +18816996168

