

Product Data

TITANEX HF1881 FOR HDPE FILM

CHARACTER HF1881 is a pelleted medium molecular weight, high density polyethylene Hexene-1 resin for tubular film extrusion. HF1881 meets the U.S. Food and Drug Administration (FDA) criteria for food contact use as specified in 21 CFR 177.1520 (c) 3.1a & 3.2a.

APPLICATIONS Grocery sacks, shopping bags, liners and thin films.

ADVANTAGES Specially designed for high extrusion rate at lower temperature, good film strength and rigidity, excellent drawdown for high quality thin film, when better strength is needed, mixing with HF0961 will provide a balance between strength and extrudability.

<u>TYPICAL RESIN PROPERTIES</u>	<u>UNIT</u>	<u>HF1881</u> ^(a)	<u>ASTM METHOD</u> ^(b)
Melt index, I ₂	g/10 min.	0.2	D 1238
Melt index, I ₂₁	g/10 min.	18	D 1238
Density	g/cm ³	0.949	D 1505

TYPICAL FILM PROPERTIES ^(c)

Tensile Strength at Break MD/TD	kg/cm ²	550/400	D 882
Ultimate Elongation MD/TD	%	350/500	D 882
1% Secant Modulus MD/TD	kg/cm ²	9300/9500	D 882
Elmendorf Tear MD/TD	g/μm	0.3/4	D 1922
Dart Impact Strength	g/μm	8	D 1709

(a) Values shown are typical and are not to be considered as specifications.

(b) ASTM test methods are latest under the Society's current procedures.

(c) Film properties are typical blown film of 17 microns extruded at 4:1 BUR.

Processing conditions

Melt temperature	: 180 - 220°C
BUR	: 4:1
Frost line height	: 7 - 12 times die diameter

LOTTE CHEMICAL TITAN (M) SDN. BHD.

Titanex® • Titanlene® • Titanzex® • Titanpro® • Titanvene®

塑料专家 www.ponci.com.cn/wxb/ +13538586433 +18816996168

