

# Product Data

## TITANZEX HI1100 FOR INJECTION MOLDING

- CHARACTER** HI1100 is a high density polyethylene for injection molding. HI1100 meets the U.S. Food and Drug Administration (FDA) criteria for food contact use as specified in 21 CFR 177.1520 (c) 3.1a & 3.2a.
- APPLICATIONS** Large sized heavy duty articles, Pallets, Crates, Industrial pails, Dustbins.
- ADVANTAGES** Excellent stiffness.

<u>TYPICAL RESIN PROPERTIES</u>	<u>UNIT</u>	<u>HI1100</u> <sup>(a)</sup>	<u>ASTM METHOD</u> <sup>(b)</sup>
Melt index	g/10 min	7	D 1238
Density	g/cm <sup>3</sup>	0.961	D 1505
Vicat Softening Point	°C	126	D 1525

### TYPICAL MECHANICAL PROPERTIES

Tensile strength at yield	kg/cm <sup>2</sup>	320	D 638
Tensile strength at break	kg/cm <sup>2</sup>	170	D 638
Elongation at break	%	30	D 638
Stiffness (Olsen)	kg/cm <sup>2</sup>	10000	D 747
Izod impact strength	kg·cm/cm	5	D 256
Shore hardness	D scale	65	D 2240

(a) Values shown are typical and are not to be considered as specifications.

(b) ASTM test methods are latest under the Society's current procedures.

Shrinkage : 2 - 5% depending on the product wall thickness and molding parameters.

LOTTE CHEMICAL TITAN (M) SDN. BHD.

Titanex® • Titanlene® • Titanzex® • Titanpro® • Titanvene®

塑料专家 [www.ponci.com.cn/wxb/](http://www.ponci.com.cn/wxb/) +13538586433 +18816996168

