



COSMOTHENE® G215

CHARACTERISTICS

COSMOTHENE G215 has excellent strength and stress cracking resistance.

APPLICATIONS

Small articles injection molding, blow bottle, bottle cap and lid.

G215 complies with U.S. FDA Regulation 21 CFR 177.1520 (C) 2.1, as long as it is used unmodified and processed according to standard manufacturing practices in the industries.

Note : Direct food contact is subjected to the extraction provisions of the regulation on the finished food contact article.

PHYSICAL PROPERTIES

ITEM	UNIT	G215	TEST METHOD
Melt Flow Rate	g/10 mins	1.5	ASTM D1238
Density	g/cm ³	0.92	ASTM D792
Tensile Strength at break	MPa	16.0	ASTM D638
Elongation	%	700	ASTM D638
Stiffness	MPa	200	ASTM D747
Melting Point	°C	108	TPC METHOD

- The figures presented are typical laboratory averages, only for reference.
- The information is based on our current knowledge, is subjected to continuous updates and is intended to suggest/ recommend product applications and to provide typical data on the related properties. It should not therefore be construed as guaranteeing any specific property of the product. TPC makes no warranty of any kind, expressed or implied, regarding the accuracy of these data.

