



COSMOTHENE® G810-S

CHARACTERISTICS

COSMOTHENE G810-S has excellent cracking resistance, processibility and small pellets

APPLICATIONS

Artificial flower and other injection molding usages.

PHYSICAL PROPERTIES

ITEM	UNIT	G810-S	TEST METHOD
Melt Flow Rate	g/10 mins	35	ASTM D1238
Density	g/cm ³	0.918	ASTM D792
Tensile Strength at break	Mpa	9.8	ASTM D638
Elongation	%	600	ASTM D638
Stiffness	Mpa	160	ASTM D747
Melting Point	°C	105	TPC METHOD

- The figures presented are typical laboratory averages, only for reference.
- The information is based on our current knowledge, is subjected to continuous updates and is intended to suggest/ recommend product applications and to provide typical data on the related properties. It should not therefore be construed as guaranteeing any specific property of the product. TPC makes no warranty of any kind, expressed or implied, regarding the accuracy of these data.

