

DELOXEN 3010

PPOm resin, 30% glass fiber reinforced for injection moulding



PROPERTY	CONDITIONS	NORMS	UNITS	VALUE
PHYSICAL PROPERTIES				
Density	-	ISO-1183	g/cm ³	1,35
MVR (280°C/5 kg)	-	ISO-1133	cm ³ /10 min	5
Linear Mould Shrinkage	-	ASTM D-955	%	0,2
Water Adsorption	23°C-Sat	ISO-62	%	0,2
THERMAL PROPERTIES				
Vicat Softening Point	VICAT B (50 N)	ASTM D-1525	°C	140
Long Term Temperature	-	Internal Method	°C	110
MECHANICAL PROPERTIES				
Impact Strength Izod Notched	23 °C	ISO-180/A	kJ/m ²	6
Impact Strength Izod Unnotched	23 °C	ISO-180/U	kJ/m ²	20
Tensile Strength at Break	23 °C	ISO-527/1-2	MPa	90
Elongation at Break	23 °C	ISO-527/1-2	%	1,7
Tensile Modulus	23 °C	ISO-527/1-2	MPa	7500

