

VAMPLEN 0024 V2 LH C

PP resin unfilled, flame retarded halogen free for injection moulding



PROPERTY	CONDITIONS	NORMS	UNITS	VALUE
PHYSICAL PROPERTIES				
Density	-	ISO-1183	g/cm ³	0,91
MVR (230°C/2,16 kg)	-	ISO-1133	cm ³ /10 min	15
Linear Mould Shrinkage	-	ASTM D-955	%	1,6
Trasversal Mould Shrinkage	-	ASTM D-955	%	1,6
Water Adsorption	23 °C-24h	ASTM D-570	%	0,02
THERMAL PROPERTIES				
Vicat Softening Point	VICAT B (50 N)	ASTM D-1525	°C	85
Heat Distortion Temperature	HDT A (1,80 MPa)	ASTM D-648	°C	55
MECHANICAL PROPERTIES				
Impact Strength Izod Notched	23 °C	ISO-180/A	kJ/m ²	10
Impact Strength Izod Unnotched	23 °C	ISO-180/U	kJ/m ²	NB
Tensile Strength at Break	23 °C	ISO-527/1-2	MPa	25
Elongation at Break	23 °C	ISO-527/1-2	%	>50
Tensile Modulus	23 °C	ISO-527/1-2	MPa	1300
ELECTRICAL PROPERTIES				
Comparative Tracking Index	-	IEC 60112	V	600



VAMPLEN 0024 V2 LH C

PP resin unfilled, flame retarded halogen free for injection moulding



FLAME RESISTANCE

Thickness 3,2 mm	-	UL 94	-	V2
Thickness 1,6 mm	-	UL 94	-	V2
Thickness 0,8 mm	-	UL 94	-	V2
GWFI (1 mm)	-	IEC 60695-2-12	°C / mm	960
GWFI (2 mm)	-	IEC 60695-2-12	°C / mm	960

