

# VAMPLEN 0024 V2 LBC GW

PP resin unfilled, flame retarded halogen free for injection moulding



PROPERTY	CONDITIONS	NORMS	UNITS	VALUE
<b>PHYSICAL PROPERTIES</b>				
Density	-	ISO-1183	g/cm <sup>3</sup>	1,04
MVR (230°C/2,16 kg)	-	ISO-1133	cm <sup>3</sup> /10 min	15
Linear Mould Shrinkage	-	ASTM D-955	%	1,2
Trasversal Mould Shrinkage	-	ASTM D-955	%	1,2
Water Adsorption	23°C-24h	ASTM D-570	%	0,02
<b>THERMAL PROPERTIES</b>				
Vicat Softening Point	VICAT B (50 N)	ASTM D-1525	°C	95
Heat Distortion Temperature	HDT A (1,80 MPa)	ASTM D-648	°C	60
Ball Pressure Test	-	IEC 60695-10-2	°C	125
Relative Temperature Index ELEC	Electric	UL 746 B	°C	110
Relative Temperature Index IMP	Impact	UL 746 B	°C	110
Relative Temperature Index STR	Strength	UL 746 B	°C	110
<b>MECHANICAL PROPERTIES</b>				
Impact Strength Izod Notched	23 °C	ISO-180/A	kJ/m <sup>2</sup>	2,5
Impact Strength Izod Unnotched	23 °C	ISO-180/U	kJ/m <sup>2</sup>	20
Tensile Strength at Break	23 °C	ISO-527/1-2	MPa	20
Elongation at Break	23 °C	ISO-527/1-2	%	>50
Tensile Modulus	23 °C	ISO-527/1-2	MPa	2200



# VAMPLEN 0024 V2 LBC GW

PP resin unfilled, flame retarded halogen free for injection moulding



ELECTRICAL PROPERTIES				
Comparative Tracking Index	-	IEC 60112	V	600
FLAME RESISTANCE				
Thickness 3,0 mm	-	UL 94	-	V2
Thickness 1,6 mm	-	UL 94	-	V2
Thickness 0,75 mm	-	UL 94	-	V2
GWFI (1 mm)	-	IEC 60695-2-12	°C / mm	850
GWFI (2 mm)	-	IEC 60695-2-12	°C / mm	850
GWIT (1 mm)	-	IEC 60695-2-13	°C / mm	775
GWIT (2 mm)	-	IEC 60695-2-13	°C / mm	775

