

VAMPLUB C 20C 3TF

PC resin, 20% carbon fiber reinforced with improved slip properties for injection moulding



PROPERTY	CONDITIONS	NORMS	UNITS	VALUE
PHYSICAL PROPERTIES				
Density	-	ISO-1183	g/cm ³	1,36
MVR (300°C/1,2 kg)	-	ISO-1133	cm ³ /10 min	15
Linear Mould Shrinkage	-	ASTM D-955	%	0,2
Trasversal Mould Shrinkage	-	ASTM D-955	%	0,5
Water Adsorption	23 °C-24h	ASTM D-570	%	0,15
THERMAL PROPERTIES				
Vicat Softening Point	VICAT B (50 N)	ASTM D-1525	°C	145
Heat Distortion Temperature	HDT A (1,80 MPa)	ASTM D-648	°C	135
Long Term Temperature	-	Internal Method	°C	135
MECHANICAL PROPERTIES				
Impact Strength Izod Notched	23 °C	ISO-180/A	kJ/m ²	8
Impact Strength Izod Unnotched	23 °C	ISO-180/U	kJ/m ²	30
Tensile Strength at Break	23 °C	ISO-527/1-2	MPa	140
Elongation at Break	23 °C	ISO-527/1-2	%	1,8
Tensile Modulus	23 °C	ISO-527/1-2	MPa	15000
ELECTRICAL PROPERTIES				
Surface Resistivity	-	ASTM D257	Ohm	10 ^{^3}
FLAME RESISTANCE				
Thickness 3,2 mm	-	UL 94	-	V1



VAMPLUB C 20C 3TF

PC resin, 20% carbon fiber reinforced with improved slip properties for injection moulding



TRIBOLOGICAL PROPERTIES

Wear Factor K	-	Thrust Washer	-	34
Coeff. of Friction	Dynamic	ASTM D-1894	-	0,16
Coeff. of Friction	Static	ASTM D-1894	-	0,22

