

DENIFORM 2010

POM resin, 20% glass fiber reinforced for injection moulding



PROPERTY	CONDITIONS	NORMS	UNITS	VALUE
PHYSICAL PROPERTIES				
Density	-	ISO-1183	g/cm ³	1,55
MVR (190°C/2,16 kg)	-	ISO-1133	cm ³ /10 min	5
Water Adsorption	23°C-Sat	ISO-62	%	0,8
THERMAL PROPERTIES				
Vicat Softening Point	VICAT B (50 N)	ASTM D-1525	°C	155
Long Term Temperature	-	Internal Method	°C	90
MECHANICAL PROPERTIES				
Impact Strength Izod Notched	23 °C	ISO-180/A	kJ/m ²	4,5
Impact Strength Izod Unnotched	23 °C	ISO-180/U	kJ/m ²	25
Tensile Strength at Break	23 °C	ISO-527/1-2	MPa	100
Elongation at Break	23 °C	ISO-527/1-2	%	3
Tensile Modulus	23 °C	ISO-527/1-2	MPa	7000

