

# DENYL 66 5010

PA66 resin 50% glass fiber reinforced for injection moulding



PROPERTY	CONDITIONS	NORMS	UNITS	VALUE
<b>PHYSICAL PROPERTIES</b>				
Density	-	ISO-1183	g/cm <sup>3</sup>	1,56
Linear Mould Shrinkage	-	ASTM D-955	%	0,2
Trasversal Mould Shrinkage	-	ASTM D-955	%	0,5
<b>THERMAL PROPERTIES</b>				
Vicat Softening Point	VICAT B (50 N)	ASTM D-1525	°C	255
Heat Distortion Temperature	HDT A (1,80 MPa)	ASTM D-648	°C	255
Long Term Temperature	-	Internal Method	°C	140
<b>MECHANICAL PROPERTIES</b>				
Impact Strength Izod Notched	23 °C	ISO-180/A	kJ/m <sup>2</sup>	12
Impact Strength Izod Unnotched	23 °C	ISO-180/U	kJ/m <sup>2</sup>	80
Tensile Strength at Break	23 °C	ISO-527/1-2	MPa	220
Elongation at Break	23 °C	ISO-527/1-2	%	2,5
Tensile Modulus	23 °C	ISO-527/1-2	MPa	17000
<b>FLAME RESISTANCE</b>				
Thickness 3,0 mm	-	UL 94	-	HB
Thickness 0,75 mm	-	UL 94	-	HB

