

VAMPGREEN Y 25G RC V0 30 1S 04 GW

PA66 post industrial recycled based injection moulding compound, 25% glass fiber reinforced, flame retarded with red phosphorus



PROPERTY	CONDITIONS	NORMS	UNITS	VALUE
PHYSICAL PROPERTIES				
Density	-	ISO-1183	g/cm ³	1,45
Linear Mould Shrinkage	-	ASTM D-955	%	0,5
Trasversal Mould Shrinkage	-	ASTM D-955	%	0,9
Water Adsorption	23°C-24h	ASTM D-570	%	0,9
THERMAL PROPERTIES				
Vicat Softening Point	VICAT B (50 N)	ASTM D-1525	°C	240
Heat Distortion Temperature	HDT A (1,80 MPa)	ASTM D-648	°C	235
Long Term Temperature	-	Internal Method	°C	130
MECHANICAL PROPERTIES				
Impact Strength Izod Notched	23 °C	ISO-180/A	kJ/m ²	7
Impact Strength Izod Unnotched	23 °C	ISO-180/U	kJ/m ²	45
Tensile Strength at Break	23 °C	ISO-527/1-2	MPa	125
Elongation at Break	23 °C	ISO-527/1-2	%	2
Tensile Modulus	23 °C	ISO-527/1-2	MPa	9000
ELECTRICAL PROPERTIES				
Comparative Tracking Index	-	IEC 60112	V	600



VAMPGREEN Y 25G RC V0 30 1S 04 GW

PA66 post industrial recycled based injection moulding compound, 25% glass fiber reinforced, flame retarded with red phosphorus



FLAME RESISTANCE

Thickness 3,2 mm	-	UL 94	-	V0
Thickness 1,6 mm	-	UL 94	-	V0
GWFI (1 mm)	-	IEC 60695-2-12	°C / mm	960
GWFI (2 mm)	-	IEC 60695-2-12	°C / mm	960
GWIT (1 mm)	-	IEC 60695-2-13	°C / mm	775
GWIT (2 mm)	-	IEC 60695-2-13	°C / mm	775

