

VAMPAMID 66 2530 VO P GW

PA66 resin 25% glass fiber reinforced, flame retarded with red phosphorus for injection moulding



PROPERTY	CONDITIONS	NORMS	UNITS	VALUE
PHYSICAL PROPERTIES				
Density	-	ISO-1183	g/cm ³	1,45
Linear Mould Shrinkage	-	ASTM D-955	%	0,6
Trasversal Mould Shrinkage	-	ASTM D-955	%	1
Water Adsorption	23°C-24h	ASTM D-570	%	0,9
THERMAL PROPERTIES				
Vicat Softening Point	VICAT B (50 N)	ASTM D-1525	°C	240
Heat Distortion Temperature	HDT A (1,80 MPa)	ASTM D-648	°C	240
Relative Temperature Index ELEC	Electric	UL 746 B	°C	120
Relative Temperature Index IMP	Impact	UL 746 B	°C	115
Relative Temperature Index STR	Strength	UL 746 B	°C	130
MECHANICAL PROPERTIES				
Impact Strength Izod Notched	23 °C	ISO-180/A	kJ/m ²	8
Impact Strength Izod Unnotched	23 °C	ISO-180/U	kJ/m ²	45
Tensile Strength at Break	23 °C	ISO-527/1-2	MPa	130
Elongation at Break	23 °C	ISO-527/1-2	%	2,1
Tensile Modulus	23 °C	ISO-527/1-2	MPa	8500
ELECTRICAL PROPERTIES				
Comparative Tracking Index	-	IEC 60112	V	600



VAMPAMID 66 2530 VO P GW

PA66 resin 25% glass fiber reinforced, flame retarded with red phosphorus for injection moulding



FLAME RESISTANCE				
Thickness 3,0 mm	-	UL 94	-	VO
Thickness 1 mm	-	UL 94	-	VO
Thickness 0,75 mm	-	UL 94	-	VO
GWFI (1 mm)	-	IEC 60695-2-12	°C / mm	960
GWFI (2 mm)	-	IEC 60695-2-12	°C / mm	960
GWIT (1 mm)	-	IEC 60695-2-13	°C / mm	775
GWIT (2 mm)	-	IEC 60695-2-13	°C / mm	775

