

VAMPAMID 66 2556 VO

PA66 resin 25% glass fiber reinforced, flame retarded with halogens, antimony free for injection moulding



PROPERTY	CONDITIONS	NORMS	UNITS	VALUE
PHYSICAL PROPERTIES				
Density	-	ISO-1183	g/cm ³	1,56
Linear Mould Shrinkage	-	ASTM D-955	%	0,5
Trasversal Mould Shrinkage	-	ASTM D-955	%	0,9
Water Adsorption	23°C-24h	ASTM D-570	%	0,7
THERMAL PROPERTIES				
Vicat Softening Point	VICAT B (50 N)	ASTM D-1525	°C	225
Heat Distortion Temperature	HDT A (1,80 MPa)	ASTM D-648	°C	230
Long Term Temperature	-	Internal Method	°C	140
MECHANICAL PROPERTIES				
Impact Strength Izod Notched	23 °C	ISO-180/A	kJ/m ²	7,5
Impact Strength Izod Unnotched	23 °C	ISO-180/U	kJ/m ²	40
Tensile Strength at Break	23 °C	ISO-527/1-2	MPa	120
Elongation at Break	23 °C	ISO-527/1-2	%	2
Tensile Modulus	23 °C	ISO-527/1-2	MPa	9500
ELECTRICAL PROPERTIES				
Comparative Tracking Index	-	IEC 60112	V	450



VAMPAMID 66 2556 V0

PA66 resin 25% glass fiber reinforced, flame retarded with halogens, antimony free for injection moulding



FLAME RESISTANCE				
Thickness 3,2 mm	-	UL 94	-	V0
Thickness 1,6 mm	-	UL 94	-	V0
Thickness 0,8 mm	-	UL 94	-	V0
GWFI (1 mm)	-	IEC 60695-2-12	°C / mm	960
GWFI (2 mm)	-	IEC 60695-2-12	°C / mm	960
GWIT (1 mm)	-	IEC 60695-2-13	°C / mm	775
GWIT (2 mm)	-	IEC 60695-2-13	°C / mm	775

