

VAMPAMID 66 0023 VO H GW

PA66 resin unfilled, flame retarded with halogens for injection moulding



PROPERTY	CONDITIONS	NORMS	UNITS	VALUE
PHYSICAL PROPERTIES				
Density	-	ISO-1183	g/cm ³	1,36
Linear Mould Shrinkage	-	ASTM D-955	%	1,6
Trasversal Mould Shrinkage	-	ASTM D-955	%	1,6
Water Adsorption	23°C-24h	ASTM D-570	%	1
THERMAL PROPERTIES				
Vicat Softening Point	VICAT B (50 N)	ASTM D-1525	°C	205
Heat Distortion Temperature	HDT A (1,80 MPa)	ASTM D-648	°C	80
Relative Temperature Index ELEC	Electric	UL 746 B	°C	140
Relative Temperature Index IMP	Impact	UL 746 B	°C	140
Relative Temperature Index STR	Strength	UL 746 B	°C	140
MECHANICAL PROPERTIES				
Impact Strength Izod Notched	23 °C	ISO-180/A	kJ/m ²	5,5
Impact Strength Izod Unnotched	23 °C	ISO-180/U	kJ/m ²	80
Tensile Strength at Break	23 °C	ISO-527/1-2	MPa	50
Elongation at Break	23 °C	ISO-527/1-2	%	>15
Tensile Modulus	23 °C	ISO-527/1-2	MPa	2800
ELECTRICAL PROPERTIES				
Comparative Tracking Index	-	IEC 60112	V	250



VAMPAMID 66 0023 VO H GW

PA66 resin unfilled, flame retarded with halogens for injection moulding



FLAME RESISTANCE

Thickness 3,0 mm	-	UL 94	-	V0
Thickness 1,5 mm	-	UL 94	-	V0
Thickness 0,8 mm	-	UL 94	-	V0
Thickness 0,4 mm	-	UL 94	-	V0
GWFI (1 mm)	-	IEC 60695-2-12	°C / mm	960
GWFI (2 mm)	-	IEC 60695-2-12	°C / mm	960
GWIT (1 mm)	-	IEC 60695-2-13	°C / mm	775
GWIT (2 mm)	-	IEC 60695-2-13	°C / mm	775

