

# VAMPLUB Y 10G 4TF V0 56

PA66 resin, 10% glass fiber reinforced with improved slip properties, flame retarded with halogens, ATO free, for injecton moulding



PROPERTY	CONDITIONS	NORMS	UNITS	VALUE
<b>PHYSICAL PROPERTIES</b>				
Density	-	ISO-1183	g/cm <sup>3</sup>	1,46
Linear Mould Shrinkage	-	ASTM D-955	%	0,6
Water Adsorption	23°C-24h	ASTM D-570	%	0,8
<b>THERMAL PROPERTIES</b>				
Vicat Softening Point	VICAT B (50 N)	ASTM D-1525	°C	210
Heat Distortion Temperature	HDT A (1,80 MPa)	ASTM D-648	°C	220
Long Term Temperature	-	Internal Method	°C	130
<b>MECHANICAL PROPERTIES</b>				
Impact Strength Izod Notched	23 °C	ISO-180/A	kJ/m <sup>2</sup>	6
Impact Strength Izod Unnotched	23 °C	ISO-180/U	kJ/m <sup>2</sup>	35
Tensile Strength at Break	23 °C	ISO-527/1-2	MPa	70
Elongation at Break	23 °C	ISO-527/1-2	%	2,5
Tensile Modulus	23 °C	ISO-527/1-2	MPa	4500
<b>ELECTRICAL PROPERTIES</b>				
Comparative Tracking Index	-	IEC 60112	V	350



# VAMPLUB Y 10G 4TF V0 56

PA66 resin, 10% glass fiber reinforced with improved slip properties, flame retarded with halogens, ATO free, for injecton moulding



## FLAME RESISTANCE

Thickness 3,2 mm	-	UL 94	-	V0
Thickness 1,5 mm	-	UL 94	-	V1
GWFI (1 mm)	-	IEC 60695-2-12	°C / mm	850
GWFI (2 mm)	-	IEC 60695-2-12	°C / mm	850
GWIT (1 mm)	-	IEC 60695-2-13	°C / mm	775
GWIT (2 mm)	-	IEC 60695-2-13	°C / mm	775

