

# Denistat A 00U 09

ABS resin unfilled, dissipative for injection moulding



PROPERTY	CONDITIONS	NORMS	UNITS	VALUE
<b>PHYSICAL PROPERTIES</b>				
Density	-	ISO-1183	g/cm <sup>3</sup>	1,04
MVR (220°C/10 kg)	-	ISO-1133	cm <sup>3</sup> /10 min	35
Linear Mould Shrinkage	-	ASTM D-955	%	0,7
Trasversal Mould Shrinkage	-	ASTM D-955	%	0,7
<b>THERMAL PROPERTIES</b>				
Vicat Softening Point	VICAT B (50 N)	ASTM D-1525	°C	90
Heat Distortion Temperature	HDT A (1,80 MPa)	ASTM D-648	°C	70
Long Term Temperature	-	Internal Method	°C	70
<b>MECHANICAL PROPERTIES</b>				
Impact Strength Izod Notched	23 °C	ISO-180/A	kJ/m <sup>2</sup>	30
Impact Strength Izod Unnotched	23 °C	ISO-180/U	kJ/m <sup>2</sup>	NB
Tensile Strength at Break	23 °C	ISO-527/1-2	MPa	30
Elongation at Break	23 °C	ISO-527/1-2	%	>10
Tensile Modulus	23 °C	ISO-527/1-2	MPa	1700
<b>ELECTRICAL PROPERTIES</b>				
Surface Resistivity	-	ASTM D257	Ohm	10 <sup>9</sup>

