

VAMPSTAT A 00U 09 V0 26

ABS resin unfilled, dissipative, flame retarded with halogens
for injection moulding



PROPERTY	CONDITIONS	NORMS	UNITS	VALUE
PHYSICAL PROPERTIES				
Density	-	ISO-1183	g/cm ³	1,22
MVR (220°C/10 kg)	-	ISO-1133	cm ³ /10 min	50
Linear Mould Shrinkage	-	ASTM D-955	%	0,7
Trasversal Mould Shrinkage	-	ASTM D-955	%	0,8
THERMAL PROPERTIES				
Vicat Softening Point	VICAT B (50 N)	ASTM D-1525	°C	85
Heat Distortion Temperature	HDT A (1,80 MPa)	ASTM D-648	°C	65
MECHANICAL PROPERTIES				
Impact Strength Izod Notched	23 °C	ISO-180/A	kJ/m ²	20
Impact Strength Izod Unnotched	23 °C	ISO-180/U	kJ/m ²	NB
Tensile Strength at Break	23 °C	ISO-527/1-2	MPa	30
Elongation at Break	23 °C	ISO-527/1-2	%	>10
Tensile Modulus	23 °C	ISO-527/1-2	MPa	1600
ELECTRICAL PROPERTIES				
Surface Resistivity	-	ASTM D257	Ohm	10 ^{^9}
FLAME RESISTANCE				
Thickness 3,2 mm	-	UL 94	-	V0
Thickness 1,6 mm	-	UL 94	-	V0
GWFI (1 mm)	-	IEC 60695-2-12	°C / mm	960
GWFI (2 mm)	-	IEC 60695-2-12	°C / mm	960

