

VAMPAMID 6 2028 V2 MF

PA6 resin, 20% glass fiber reinforced, flame retarded halogen free for injection moulding



PROPERTY	CONDITIONS	NORMS	UNITS	VALUE
PHYSICAL PROPERTIES				
Density	-	ISO-1183	g/cm ³	1,33
Linear Mould Shrinkage	-	ASTM D-955	%	1,1
Trasversal Mould Shrinkage	-	ASTM D-955	%	0,9
Water Adsorption	23°C-24h	ASTM D-570	%	1,3
THERMAL PROPERTIES				
Vicat Softening Point	VICAT B (50 N)	ASTM D-1525	°C	205
Relative Temperature Index ELEC	Electric	UL 746 B	°C	120
Relative Temperature Index IMP	Impact	UL 746 B	°C	65
Relative Temperature Index STR	Strength	UL 746 B	°C	105
MECHANICAL PROPERTIES				
Impact Strength Izod Notched	23 °C	ISO-180/A	kJ/m ²	4
Impact Strength Izod Unnotched	23 °C	ISO-180/U	kJ/m ²	35
Tensile Strength at Break	23 °C	ISO-527/1-2	MPa	70
Elongation at Break	23 °C	ISO-527/1-2	%	5
Tensile Modulus	23 °C	ISO-527/1-2	MPa	4800
ELECTRICAL PROPERTIES				
Comparative Tracking Index	-	IEC 60112	V	600



VAMPAMID 6 2028 V2 MF

PA6 resin, 20% glass fiber reinforced, flame retarded halogen free for injection moulding



FLAME RESISTANCE

Thickness 3,0 mm	-	UL 94	-	V2
Thickness 1,5 mm	-	UL 94	-	V2
Thickness 0,8 mm	-	UL 94	-	V2
GWFI (1 mm)	-	IEC 60695-2-12	°C / mm	960
GWFI (2 mm)	-	IEC 60695-2-12	°C / mm	960

