

# VAMPAMID 6 0036 V2

PA6 resin unfilled, flame retarded with halogens, antimony free, for injection moulding



PROPERTY	CONDITIONS	NORMS	UNITS	VALUE
<b>PHYSICAL PROPERTIES</b>				
Density	-	ISO-1183	g/cm <sup>3</sup>	1,25
Linear Mould Shrinkage	-	ASTM D-955	%	1,4
Trasversal Mould Shrinkage	-	ASTM D-955	%	1,4
Water Adsorption	23°C-24h	ASTM D-570	%	1,5
<b>THERMAL PROPERTIES</b>				
Vicat Softening Point	VICAT B (50 N)	ASTM D-1525	°C	195
Long Term Temperature	-	Internal Method	°C	120
<b>MECHANICAL PROPERTIES</b>				
Impact Strength Izod Notched	23 °C	ISO-180/A	kJ/m <sup>2</sup>	5
Impact Strength Izod Unnotched	23 °C	ISO-180/U	kJ/m <sup>2</sup>	65
Tensile Strength at Break	23 °C	ISO-527/1-2	MPa	60
Elongation at Break	23 °C	ISO-527/1-2	%	10
Tensile Modulus	23 °C	ISO-527/1-2	MPa	3700
<b>ELECTRICAL PROPERTIES</b>				
Comparative Tracking Index	-	IEC 60112	V	350



# VAMPAMID 6 0036 V2

PA6 resin unfilled, flame retarded with halogens, antimony free, for injection moulding



FLAME RESISTANCE				
Thickness 3,2 mm	-	UL 94	-	V2
Thickness 1,6 mm	-	UL 94	-	V2
Thickness 0,8 mm	-	UL 94	-	V2
GWFI (1 mm)	-	IEC 60695-2-12	°C / mm	850
GWFI (2 mm)	-	IEC 60695-2-12	°C / mm	850
GWIT (1 mm)	-	IEC 60695-2-13	°C / mm	775
GWIT (2 mm)	-	IEC 60695-2-13	°C / mm	775

