

H100EY

HOMOPOLYMER

FOR TQ (TUBULAR WATER QUENCH) FILM

Repol H100EY is PP homopolymer grade recommended for use in TQ (Tubular Water Quench) Film. The grade is specially formulated with slip and antiblock additives.

BIS Designation Code: IS 10951-1-NBH-B

Typical Characteristics

Property	Test Method	Unit	Typical Value*
----------	-------------	------	----------------

Melt Flow Rate (230 ° C/2.16 kg)	ASTM D1238	g/10 min	11.0
----------------------------------	------------	----------	------

Density	ASTM D792	g/ cc.	0.90
---------	-----------	--------	------

FILM PROPERTIES (TQPP FILM)

Tensile Strength at Yield (MD / TD)	ASTM D882	MPa	22 / 19
-------------------------------------	-----------	-----	---------

Tensile Strength at Break (MD / TD)	ASTM D882	MPa	32 / 30
-------------------------------------	-----------	-----	---------

Elongation at Break (MD / TD)	ASTM D882	%	580 / 750
-------------------------------	-----------	---	-----------

Haze – 20 μ / 40 μ	ASTM D1003	%	3.0 / 7.0
--------------------	------------	---	-----------

Gloss @ 20 ° / 60 °	ASTM D2457	GU	70 / 115
---------------------	------------	----	----------

Coefficient of friction (St / Kn)	ASTM D1894	---	0.25 / 0.20
-----------------------------------	------------	-----	-------------

* Typical values. Not to be taken as specifications

Mechanical and optical properties are on 40 microns. Film processed on TQPP film plant with quench water temperature of 15 ° C.

Typical Processing Conditions

Extrusion temperatures: 200 – 240 ° C

Cooling water temperature: 15 – 25 ° C

Note: Processing parameters mentioned above are for reference only and not to be considered as specifications. They may vary based on the product to be manufactured.

Applications

Textile overwrap films, Garment bags, Snack food, Grocery and General-purpose packaging.

Regulatory Information

The product complies with Indian Standard IS 10910 on “Specification for polypropylene and its copolymers for safe use in contact with foodstuffs, pharmaceuticals and drinking water. It also conforms to IS 16738:2018 on positive list of constituents for polypropylene, polyethylene and their copolymers for its safe use in contact with foodstuffs and pharmaceuticals. The grade and the additives incorporated in it also comply with FDA:CFR Title 21,177.1520, Olefin polymers.

Not to be used in the manufacture of Single Use Plastic (SUP) items prohibited under PWM Rules, 2016.

Storage Recommendations

Bags should be stored in dry / closed conditions at temperatures below 50°C and protected from UV / direct sunlight.